

2006

Development and characterisation of polyaniline - carbon nanotube conducting composite fibres

Vahid Mottaghitlab
University of Wollongong

UNIVERSITY OF WOLLONGONG

COPYRIGHT WARNING

You may print or download ONE copy of this document for the purpose of your own research or study. The University does not authorise you to copy, communicate or otherwise make available electronically to any other person any copyright material contained on this site. You are reminded of the following:

This work is copyright. Apart from any use permitted under the Copyright Act 1968, no part of this work may be reproduced by any process, nor may any other exclusive right be exercised, without the permission of the author.

Copyright owners are entitled to take legal action against persons who infringe their copyright. A reproduction of material that is protected by copyright may be a copyright infringement. A court may impose penalties and award damages in relation to offences and infringements relating to copyright material. Higher penalties may apply, and higher damages may be awarded, for offences and infringements involving the conversion of material into digital or electronic form.

Unless otherwise indicated, the views expressed in this thesis are those of the author and do not necessarily represent the views of the University of Wollongong.

Recommended Citation

Mottaghitlab, Vahid, Development and characterisation of polyaniline - carbon nanotube conducting composite fibres, PhD thesis, School of Mechanical, Materials and Mechatronic Engineering, University of Wollongong, 2006. <http://ro.uow.edu.au/theses/491>

NOTE

This online version of the thesis may have different page formatting and pagination from the paper copy held in the University of Wollongong Library.

UNIVERSITY OF WOLLONGONG

COPYRIGHT WARNING

You may print or download ONE copy of this document for the purpose of your own research or study. The University does not authorise you to copy, communicate or otherwise make available electronically to any other person any copyright material contained on this site. You are reminded of the following:

Copyright owners are entitled to take legal action against persons who infringe their copyright. A reproduction of material that is protected by copyright may be a copyright infringement. A court may impose penalties and award damages in relation to offences and infringements relating to copyright material. Higher penalties may apply, and higher damages may be awarded, for offences and infringements involving the conversion of material into digital or electronic form.

**DEVELOPMENT AND CHARACTERISATION OF
POLYANILINE - CARBON NANOTUBE CONDUCTING
COMPOSITE FIBRES**

A thesis submitted in fulfillment of the
requirements for the award of the degree

DOCTOR OF PHILOSOPHY

From

UNIVERSITY OF WOLLONGONG



by

VAHID MOTTAGHITALAB

(B.Sc. Chemical Engineering; M.Sc. Polymer Engineering)

School of Material, Mechanical and Mechatronic Engineering

JUNE 2006

IN THE NAME OF ALLAH, THE MOST GRACIOUS, THE MOST MERCIFUL

This thesis is dedicated to:

My wife: Mahin

My son: Amir Reza

*For their love, support and patience
and my Mother for her encouragement,
especially in memory of my father*

and

To My Brothers

THESIS CERTIFICATION

I, Vahid Mottaghitalab, declare that this thesis, submitted in fulfillment of the requirements for the award of Doctor of Philosophy, in the School of Material, Mechanical and Mechatronic Engineering, Faculty of Engineering, University of Wollongong, is wholly my own work unless otherwise referenced or acknowledged. The thesis was completed under the supervision of Prof. Geoffery. M. Spinks and Prof. Gordon. G. Wallace and has not been submitted for qualification at any other academic institution.

Vahid Mottaghitalab

JUNE 2006

ACKNOWLEDGMENTS

The author would like to express his sincere gratitude to Prof. Geoffery. M. Spinks for his supervision, encouragement, guidance and inspiration provided during the course of this research. I would also like to express my sincere thanks to Prof. Gordon. G. Wallace for his advice, encouragement and critical review of several aspects of this study and providing the necessary facilities.

The author also wishes to express his sincere thanks for helpful contributions made by the following professionals during the period of this study:

Dr Peter Innis for his very helpful technical collaboration, Dr Chee O Too for supportive role in preparation of experimental requirement and safety , Dr Syed Ashraf for synthesis of exclusive ionic liquids, Dr Phil Whitten for his impressive comments and suggestions.

I also deeply appreciate from Dr Simon Moulton and Dr Violteta Misoska helpful assistance in electron microscopy.

I also gratefully acknowledge helpful assistance of the students at the Intelligent Polymer Research Institute, Scott Mc Govern, Dr George Tsekouras, Yanzhe Wu and Dr Binbin Xi who always enthusiastically shared their excellent ideas and allocated valuable time for removing of obstacles.

Special thanks also to Mehrdad Bahrami for running of actuation tests and Dr C.Y .Wang for achievement of the experiment in battery tests. I would like to address the administrative help and support of Phil Smugreski.

I also would like to thank academic staff in the School of Materials, Mechanical and Mechatronic Engineering, especially Chris Lukey and David Wexler for their laboratory

assistance and also, Nick Mackie and Greg Tillman for their kind assistance in electron microscopy .

The author also would like to appreciate Mr Steve Cooper and Mr Peter Sarah in science workshop who their enthusiasm for assisting of students was enormous.

The author wishes to thank Dr Saied Sotanian and Dr Jossip Hovart for their contributions in transport measurement tests. The assistance provided by the Faculty of Engineering, University of Wollongong is also appreciated.

I would also like to acknowledge with sincere appreciation, the financial support of the Ministry of Science, Research and Technology of the Islamic Republic of Iran and University of Guilan.

Most importantly, I would like to express my deepest thanks to me and my wife parents and members of our family in IRAN who have provided continued support throughout this study and indeed for our my entire life. This study would not have been finished without support, encouragement of my wife and son.

PUBLICATIONS

Published Paper:

1. **V. Mottaghitalab**, G. M. Spinks and G. G. Wallace, The influence of carbon nanotubes on mechanical and electrical properties of polyaniline fibres, *Synthetic Metals*, 152, **(2005)**, 77-80.
2. G. M. Spinks, **V. Mottaghitalab**, M. Bahrami-Samani, P. G. Whitten and G. G. Wallace, Carbon Nanotube Reinforced Polyaniline Composite Fibres for High Strength Artificial Muscles, *Advanced Materials*, 18, **(2006)**, 637.

In Press

1. **V. Mottaghitalab**, B. Xi, G. M. Spinks and G. G. Wallace, Polyaniline Fibres Containing Single Walled Carbon Nanotubes: Enhanced Performance Artificial Muscles, *Synthetic Metals*. **(2006)**.
2. **V. Mottaghitalab**, G. M. Spinks and G. G. Wallace, The development and characterization of polyaniline - single walled nanotube composite fibres using 2-acrylamido-2 methyl -1-propane sulfonic acid (AMPSA) through one step wet spinning process, *Polymer*, **(2006)**.

Submitted to Journals:

1. C. Y. Wang, **V. Mottaghitalab**, C. O. Too, G. M. Spinks and G. G. Wallace, Investigation of Polyaniline fibre as battery material in ionic liquid, *Journal of power source*, **(2006)**.

3. B. Xi, V.T. Truong, **V. Mottaghitalab**, P. Whitten, G. M. Spinks, G. G. Wallace, “ Actuation behavior of polyaniline films and tubes prepared by the phase inversion technique”, Submitted , Smart Mater. and Struct.(2005)

Conference papers:

1. **V. Mottaghitalab**, B. Xi, G. M. Spinks and G. G. Wallace, “The influence of carbon nanotubes on mechanical, electrical and electrochemical properties of polyaniline fibre”, ICSM, Wollongong, Australia, **2004**, Session: Electronic Fibres and Other Unconventional Substrates.
2. **V. Mottaghitalab**, B. Xi, G. M. Spinks and G. G. Wallace, Polyaniline-single wall nanotube composite fibre: opportunities and challenges, Umist, Manchester, UK, **(2004)**, session 7a-Nanostructured fibres I.
3. **V. Mottaghitalab**, G. M. Spinks and G. G. Wallace, A. R. Wilson, Polyaniline-nanotube multifunctional fibre: capabilities toward the manufacturing of smart fabric, 5648, SPIE, Sydney, Australia, **(2004)**.385-396.
4. G. M. Spinks, **V. Mottaghitalab**, Binbin Xi, P. Whitten, G. Wallace, S. J. Kim, S. R. Shin and S. I. Kim, Carbon Nanotube Reinforcement of Conducting Polymers and Hydrogels for High Strength Actuators, MRS Fall Meeting, W6.2/V7.2, Boston , MA ,USA, **(2005)**.
5. G. Spinks, B. Xi, T. Campbell, P. Whitten, **V. Mottaghitalab**, M. Bahrami Samani and G. G. Wallace, In pursuit of high-force/high-stroke conducting polymer actuators (Invited Paper), Proceedings of SPIE-The International Society for Optical Engineering, 5759,**(2005)**, 314-321.

6. G. G. Wallace, **V. Mottaghitalab**, S. E. Moulton and a. G. M. Spinks., Synthesis and properties of organic, electronically conducting fibres: a platform for electronic textiles, Fr C3.2, Queenstown, New Zealand, **(2005)**.
8. B. Xi, V.-T. Truong, **V. Mottaghitalab**, P. Whitten, G. M. Spinks and G. G. Wallace, Ed: S. F. Al-Sarawi, Actuation behaviour of polyaniline films and tubes prepared by phase inversion technique, 5649, SPIE, Sydney, Australia, **(2005)**.436-444.

Manuscript in preparation:

1. **Vahid Mottaghitalab**, Philip G. Whitten, Geoffrey M. Spinks and Gordon G. Wallace , Nanotube orientation and load transfer in Polyaniline /Single Walled Carbon Nanotube Composite Fibre
2. **V. Mottaghitalab**, B. Xi, G. M. Spinks and G. G. Wallace, The study of electrical behavior of PANi- AMPSA fibre filled with CNTs: the enhanced metallic transport,

ABSTRACT

The present study describes methods for development and characterization of conducting electroactive polymer (CEP) fibre consisting of polyaniline (PAni) and single walled carbon nanotubes (SWNTs) which have potential applications as electronic devices to form building blocks of electronic textiles. The conducting composite fibres of PAni-SWNT were developed respectively using two steps (acid doping after fibre spinning) and one step methods (doping during preparation of spinning solution). The effectiveness of nanotube inclusion for improvement of mechanical, electrical and electrochemical properties was studied in each method. During development of the fibres, techniques such as UV-Vis-NIR, Raman spectroscopy, Dynamic light scattering and viscometry were used to characterise the quality of dispersion and spinning solutions. It has been shown that the N,N'-dimethyl propylene urea (DMPU) and dichloro acetic acid (DCAA) as solvents respectively for PAni in base and salt form are able to effectively disperse the pristine SWNTs to reach percolation level. The addition of nanotubes changes the rheological behavior of neat PAni spinning solution from a Newtonian to non-Newtonian shear thinning fluid based on power law regime which reflects nanotube-nanotube and/or nanotube-polymer physical entanglement. Several techniques including DMA, DSC, SEM, TEM, FIB, Raman spectroscopy, CV and four point probe electrical conductivity measurement were employed to characterize the various properties of the solid fibre. In both, one step or two steps methods, fibres containing SWNTs have superior tensile strength and elastic modulus compared with neat PAni fibre. The inclusion of SWNTs to PAni, however, decreases the elongation at break. These outcomes directly can be

attributed to physical and/or chemical interfacial interaction between well distributed SWNTs bundles and the PAni matrix. The addition of nanotubes to the PAni matrix also increases the electrical conductivity and enhances the electrochemical redox process. However, the two step method was found to have some problem include low spinning rate, low flexibility and low conductivity and insufficient charge transfer along the fibre to be working electrode. These disadvantages were diminished by faster spinning of PAni-ES/2-acrylamido-2 methyl -1-propane sulfonic acid (AMPSA)/SWNT using the one step process with more than 5 times stretching ratio. An electronic conductivity percolation threshold of ~ 0.35 % w/w SWNTs was determined with fibres possessing electronic conductivity up to $\sim 750 \text{ Scm}^{-1}$. The well defined electrochemical window for neat PAni-ES/AMPSA fibre and its composite containing SWNT either in aqueous or ionic liquid electrolyte, with wider electrochemical window, confirms the ease of charge transport through a new conduction path for the fibre formed from salt structure, which was enhanced by addition of nanotubes. The ultimate tensile strength, elastic modulus and elongation at break of PAni-ES/AMPSA/SWNT fibres containing 0.76 % w/w nanotubes respectively were obtained $255 \pm 32 \text{ Mpa}$, $7.3 \pm 0.4 \text{ GPa}$ and 4 ± 1 % compared with $170 \pm 22 \text{ MPa}$, $3.4 \pm 0.4 \text{ GPa}$ and 9 ± 3 % for PAni-ES/AMPSA fibre. The quantitative analysis of nanotube orientation and detection of load transfer from matrix to nanotubes were investigated in PAni-ES/AMPSA/SWNT composite fibre using Raman spectroscopy. It has been found that thermal stretching of as spun fibre mostly orients the nanotubes in a range of about $\pm 30^\circ$ versus fibre axis which extremely increase the Herman orientation factor from 0.02 for as spun fibre to 0.43 for the 5x drawn fibre. Moderate orientation and Raman shift about 90- 130 cm^{-1} in D* band of SWNT also can

be correlated to effective but not perfect load transfer between PANi matrix and nanotubes. The result of temperature dependent electrical conductivity data was shown that the higher conductivity of PANi-ES/AMPSA/SWNT composite fibre compared to neat PANi-ES/AMPSA fibre also can be described by improvement of the metallic property in the crystalline areas and boosting of the metallic disorder contribution in amorphous area. The consequence of improvement of mechanical, electrical and electrochemical properties were a benefit for applying of PANi/ES-AMPSA fibre and its composite having SWNT in applications as actuator, power source and sensor. While the fibres showed great promise as actuators, their response as batteries and temperature/humidity sensors was limited. The significant improvement was observed in actuator strength in excess of 100 MPa and work-per-cycle of over 300 kJ/m³ through the incorporation of small amounts of SWNTs as reinforcement in the PANi matrix. This performance is 3 times higher than previously produced conducting polymer actuators and exceeds skeletal muscle in terms of stress generation by 300 times. PANi-ES/AMPSA/SWNT exhibited a higher charge/discharge capacity (12.4/11.2 mAhg⁻¹) compared with the neat PANi-ES/AMPSA (4.5/4.1 mAhg⁻¹). All the results show that solid polyaniline fibre can be used directly as electrode in ionic liquid of EMI.TFSI for wearable power source system. However its current performance is still well below conventional rechargeable battery systems. PANi fibre and its SWNT composite showed a nonlinear response with some delay to temperature signals. The PANi fibre incorporated with SWNTs showed lower sensitivity to change in humidity pulse compared with neat PANi fibre. This behavior has good opportunity for application in conducting yarn that

needs the lowest variability in conductivity for transferring of electrical signal but clearly is not favored for sensing of humidity.

Abbreviations

Ch	Chiral vector
MWNT	multi wall carbon nanotubes
n	Power law index
NIBS	Non invasive backscattering
NIR	near infra red
NMP	N- methyl pyrrolidinone
n_R	The solvent refractive index
Nylon	11 - poly ω -aminoundecanoyl
ODF	Orientation distribution function
PAN	Polyacrylonitrile
PAni	Polyaniline
PBO	Poly butyl oxide
PGB	Pernigraniline base
Pi (cos θ)	The Legendre polynomial of degree i
$\langle P_2(\cos\theta) \rangle$	The average amount of $P_2(\cos\theta)$
$\langle P_4(\cos\theta) \rangle$	The average amount of $P_4(\cos\theta)$
POT	polyoctylthiophene
PPMS	Physical property measurement system
PPy	Polypyrrole
Psi	Pound per square inch
PT	Polythiophene
PVA	Poly vinyl alcohol
Q	volumetric flow rate (cm ³ /min)
R	Resistance(ohm)
RBM	Resonance breathing mode
S	Cross sectional area of fibre (cm ²)
SEM	Scanning electron microscopy

SWNT	single wall carbon nanotubes
$S\sigma$	the critical exponent at percolation
T	Temperature (K, °C)
TEM	Transmission electron microscopy
T_g	glass transition temperature (°C)
TGA	Thermogravimetric analysis
TM	Tangential mode (G band)
TPa	Tera pascal
T_t and T_s	tunneling parameters for transport model(K)
V	Voltage (V, mV)
V_d	Drawing velocity (m/min)
V_i	Injection rate (g/min)
V_t	Take up velocity (m/min)
α	Chiral angle
γ	Shear rate (s^{-1})
δ_b	Tensile strength at break (MPa)
$\epsilon_{c,m,f}$	Expected actuator strain of composite, matrix or filler
ϵ_b	Elongation at break (%)
η	Viscosity (mPa.s=cP)
η_0	Zero shear viscosity (mPa.s=cP)
θ	The scattering angle of laser beam
θ°	The angle between nanotubes and fibre axis
λ_2 and λ_4	The arbitrary parameter of orientation function
λ_0	The vacuum wavelength of the laser
ρ	Density (g/cm ³)
ρ_i	Resistivity of a portion either amorphous or crystalline
σ	Conductivity (S/cm)
ϕ	Spin draw ratio
ϕ_{th}	Thermal draw ratio

ψ	The angle between the polarization plane and the fibre axis
v_i	Volume fraction of component i
ω	SWNTs mass fraction in the solid fibre
ω_1	The contribution of metallic resistivity in bulk resistivity
ω_2	The contribution of nonmetallic resistivity in bulk resistivity
ω_c	critical weight percentage of SWNT at percolation
ω_p	weight fraction of polymer with regards to solvents

Table of Content

DEDICATION	II
CERTIFICATION.....	III
ACKNOWLEDGMENTS.....	IV
PUBLICATIONS.....	VI
ABSTRACT.....	IX
ABBREVIATIONS.....	XIII
LIST OF FIGURES	XXVI
LIST OF TABLES.....	XXXVIII
LIST OF SCHEMES.....	XLII

1. CHAPTER ONE.....1

General Introduction

1.1. Introduction	2
1.2. Motivation.....	2
1.3. The aims of the project.....	9
1.4. References.....	12

2. CHAPTER TWO.....17

Literature Review

2.1. The chemical structure of Polyaniline.....	18
2.1.1. The solubility of polyaniline.....	20
2.1.2. Aggregation and gel formation of polyaniline solution.....	21

2.1.3.	The solubility of PANi doped with sulfonic acid in organic acid.....	24
2.2.	Carbon Nanotubes.....	26
2.2.1.	Discovery.....	26
2.2.2.	Structure of carbon nanotubes.....	28
2.2.3.	The physical properties of SWNTs.....	29
2.2.3.1.	Aspect ratio.....	29
2.2.3.2.	Mechanical properties	30
2.2.3.3.	Electrical properties.....	31
2.2.4.	Properties and applications of self assembled SWNT material.....	32
2.2.5.	SWNT-CEP composites.....	33
2.3.	Wet spinning of Polyaniline (PANi).....	35
2.3.1.	General description of the wet spinning process.....	35
2.3.2.	A literature review for PANi fibre formation.....	37
2.4.	References.....	44

3. CHAPTER THREE.....52

General Experimental Techniques

3.1.	Introduction.....	53
3.2.	Preparation of spinning solution using ex-situ approach.....	54
3.3.	Characterisation of spinning solution.....	56
3.3.1.	Elemental analysis.....	56
3.3.2.	Dynamic Light Scattering (DLS).....	56
3.3.2.1.	Theoretical background.....	56

3.3.2.2.	Sample preparation.....	57
3.3.2.3.	The measurement description.....	58
3.3.3.	Viscometry.....	59
3.3.4.	UV-Vis and UV-Vis- NIR spectroscopy.....	60
3.4.	General description of spinning process.....	61
3.4.1.	Spinning apparatus.....	61
3.4.2.	Drawing.....	63
3.5.	Techniques for characterisation of solid fibre.....	65
3.5.1.	Four probe electrical conductivity.....	65
3.5.2.	Cyclic voltammetry.....	66
3.5.3.	Dynamic mechanical analysis.....	68
3.5.3.1.	Stress-strain (Mechanical test) in strain rate mode.....	68
3.5.3.2.	Creep mode.....	69
3.5.3.3.	Viscoelasticity test.....	70
3.5.4.	Differential scanning calirometry.....	71
3.5.5.	Raman spectroscopy.....	71
3.5.6.	Scanning Electron Microscopy.....	72
3.5.7.	Transmission electron Microscopy.....	74
3.6.	References.....	75
4.	CHAPTER FOUR.....	76

Development and Characterisation of Polyaniline (Leucoemeraldine base) / Single Walled Carbon Nanotubes Composite Fibre Prepared Using a Two Step Process

4.1.	Introduction.....	77
4.2.	Experimental.....	78
	4.2.1. Materials and reagents.....	78
	4.2.2. Instrumentation.....	78
	4.2.3. Comparison of the ability of NMP and DMPU to disperse SWNTs.....	79
	4.2.4. Influence of polyaniline addition on the degree of SWNT aggregation...	80
	4.2.5. Use of DMPU for dispersing SWNTs at higher concentrations.....	80
	4.2.6. Preparation of spinning solution.....	80
	4.2.7. The fibre spinning process.....	81
	4.2.7.1. Effect of coagulation bath composition.....	82
	4.2.7.2. Effect of take up velocity.....	82
	4.2.8. Effect of CNT content.....	82
	4.2.9. Post spinning treatments.....	83
4.3.	Results and discussions.....	83
	4.3.1. The characterisation of SWNTs.....	83
	4.3.1.1. Elemental analysis.....	83
	4.3.1.2. Raman spectroscopy of the bulk SWNTs.....	84
	4.3.2. Characterisation of SWNT dispersions.....	85
	4.3.2.1. UV-visible – NIR spectroscopy.....	85
	4.3.2.2. Dynamic Light Scattering.....	88
	4.3.2.3. Viscosity of SWNT/DMPU dispersions.....	91
	4.3.3. Viscometry of PANi-(LEB)-SWNT-DMPU spinning solution.....	92
	4.3.4. The effect of fibre spinning parameters on PANi/SWNT morphology.....	98

4.3.4.1. Influence of solvent in the coagulation bath on morphology of as spun fibre.....	99
4.3.4.2. The influence of take up velocity on morphology.....	100
4.3.5. Thermal transition temperatures in as spun fibre.....	102
4.3.6. Thermal stretching.....	103
4.3.7. Mechanical properties of thermally stretched PANi/SWNT fibres.....	105
4.3.8. Flexibility of PANi/SWNT composite fibres.....	111
4.3.9. Raman spectroscopy of PANi/SWNTs composite fibres.....	112
4.3.10. Electrical properties of PANi/SWNTs fibres.....	116
4.3.10.1. Electrical properties of PANi/SWNTs fibres before acid doping..	117
4.3.10.2. Electrical properties of PANi/SWNTs fibres after acid doping....	120
4.3.11. Cyclic voltammetry of PANi/SWNTs composite fibres.....	121
4.4. Conclusions.....	123
4.5. References.....	126

5. CHAPTER FIVE.....130

Development and Characterisation of PANi/SWNTs Composite Fibres Using 2-Acrylamido-2 Methyl -1-Propane Sulfonic Acid and a One Step Wet Spinning Process.

5.1 Introduction.....	131
5.2 Experimental.....	132
5.2.1 Materials and Reagents.....	132

5.2.2	Instrumentation.....	132
5.2.3	Characterisation of SWNT dispersions.....	136
5.2.3.1	DCAA versus DMPU as solvent.....	136
5.2.3.2	Influence of AMPSA on degree of SWNT aggregation.....	136
5.2.3.3	Ability of DCAA to disperse higher concentration of SWNT....	137
5.2.4	Preparation of composite spinning solutions.....	137
5.2.5	The fibre spinning process.....	139
5.3	Results and discussion.....	140
5.3.1	SWNTs dispersions.....	140
5.3.1.1	UV-Vis– NIR spectroscopy of SWNT dispersions.....	140
5.3.1.2	Influence of AMPSA on degree of SWNT aggregation in DCAA.....	141
5.3.1.3	Effect of sonication time on SWNTs agglomeration in DCAA...	143
5.3.1.4	Effect of SWNT concentration on aggregation of SWNTs in DCAA	145
5.3.2	Characterisation of spinning solutions.....	147
5.3.2.1	Determination of suitable PAni/AMPSA composition.....	147
5.3.2.2	Viscometry of PAni-ES/AMPSA/SWNTs-DCAA spinning solutions.....	149
5.3.3	Preparation and characterisation of composite fibres	151
5.3.3.1	Morphological properties of PAni-ES/AMPSA/SWNT as spun fibres.....	151

5.3.3.2	Morphological properties of thermally stretched PANi-ES/AMPSA/SWNT.....	153
5.3.4	The mechanical properties of composite fibres.....	156
5.3.5	Thermal analysis of the PANi-ES/AMPSA/SWNT composite fibres.....	160
5.3.6	Electrical conductivity of PANi-ES/AMPSA-SWSNT composite fibres.....	164
5.3.7	Raman spectroscopy of PANi-ES/AMPSA/SWNTs fibres.....	166
5.3.8	Cyclic Voltammetry.....	171
5.3.8.1	Cyclic voltammetry of PANi-ES/AMPSA/SWNTs composite fibres in HCl(aq).....	172
5.3.8.2	Cyclic voltammetry of PANi-ES/AMPSA/SWNTs composite fibres in ionic liquid electrolyte.....	173
5.4	Conclusions.....	178
5.5	References.....	180

6. CHAPTER SIX.184

The Understanding Of the Mechanism of Strength Increase in the PANi-ES/AMPSA/ SWNT Composite Fibre

6.1.	Introduction.....	185
6.2.	Experimental.....	186
6.2.1.	Materials.....	186
6.2.2.	Instrumentation.....	186
6.3.	Results and discussion.....	187

6.3.1. SWNTs orientation.....	187
6.3.2. Load transfer Mechanism.....	200
6.4. Conclusion.....	203
6.5. References.....	205

7. CHAPTER SEVEN.....207

Charge Transport Regime in the PAni-ES/AMPSA/SWNT Composite Fibre

7.1. Introduction.....	208
7.2. Experimental.....	210
7.2.1. Material.....	210
7.2.2. Sample preparation	210
7.2.3. Instrumental.....	211
7.3. Results and discussion.....	211
7.3.1. Electrical transport analysis.....	211
7.3.2. Heterogeneous model.....	215
7.4. Conclusion.....	222
7.5. References.....	224

8. CHAPTER EIGHT.....226

The Preliminary Studies into Applications of PAni-ES/AMPSA/SWNT Fibres

8.1. Introduction.....	227
------------------------	-----

8.1.1.	Actuators: recent development and general requirement.....	227
8.1.2.	PAni fibre electrode for application in rechargeable battery.....	229
8.1.3.	Sensitivity to temperature and humidity.....	230
8.2.	Experimental.....	231
8.2.1.	The actuation tests.....	231
8.2.1.1.	Materials and reagents.....	231
8.2.1.2.	Instrumentation.....	232
8.2.2.	Electrode material for rechargeable battery.....	233
8.2.2.1.	Materials and reagents.....	233
8.2.2.2.	Fabrication of polymer electrode.....	233
8.2.2.3.	Electrochemical characterisation.....	233
8.2.3.	Tests for sensitivity to change of temperature and humidity.....	234
8.2.3.1.	Material and reagents.....	234
8.2.3.2.	Instrumentation.....	235
8.3.	Results and discussion.....	236
8.3.1.	Actuation behavior.....	236
8.3.2.	Performance of PAni-ES/AMPSA and its composite containing SWNTs fibres as electrode material in rechargeable battery.....	243
8.3.2.1.	Charge/discharge characteristics.....	243
8.3.2.2.	Cycle life.....	245
8.3.3.	Performance of PAni-ES/AMPSA fibres with and without SWNTs as humidity and temperature sensors.....	246
8.3.3.1.	Sensitivity to temperature.....	246

8.3.3.2. Sensitivity to relative humidity (% R.H.).....	248
8.4. Conclusions.....	250
8.5. References.....	252
9. CHAPTER NINE.....	256

General Conclusion

LIST OF FIGURES

Figure 1.1. U.S. Smart and Interactive Textile market by application segment, 2003-2009 (\$ Millions)	8
Figure 1.2. The architecture of electronic textile based on component and function.....	9

Figure 2.1. The tubular structure of graphene layers of SWNT.....	27
Figure 2.2. Different arrangements of nanotubes (●) semiconducting (n,0) or (m,n) (○) metallic (n,n) or (m,n) [n-m = 3q] , q is integer.....	28
Figure 2.3. Schematic of the experimental setup used to make CNT fibres.....	33
Figure 2.4. Schematic showing the set up used for wet spinning of fibres.....	36

Figure 3.1. Schematic of sonication unit for dispersion of nanotubes in the solvent.....	55
Figure 3.2. The schematic of blending unit for mixing of PANi and SWNT dispersion...	56
Figure 3.3. Schematic diagram showing the measurement position for (a) small, weakly scattering samples and for (b) concentrated, opaque samples.....	57
Figure 3.4. The picture of spinning line apparatus has been used in this study (a) whole apparatus (b) pressure vessel (c) take up and drawing roller (d) spinneret...	62
Figure 3.5. The experimental set up used for cyclic voltammetry (a) cell set up (b) instrumental set up.....	67
Figure 3.6. The SEM pictures obtained using (a) Hitach- S900 from internal microstructure (b) Leica 440 from circular cross section.....	73

Figure 3.7. The images obtained from a sample of polyaniline fibre from different angle using FIB.....	74

Figure 4.1. Raman spectrum of bulk SWNTs ($\lambda_{exc}=632.8$ nm).....	84
Figure 4.2. UV-Vis NIR spectra of SWNT (0.01% w/w) in (a) DMPU and (b) NMP after 2hrs sonication (A, B, C: refer to table 4.4).....	86
Figure 4.3. Hydrodynamic diameter distribution of SWNT bundles in DMPU for different sonication times (triangle) 30 min (square) 60 min (circle) 120 min.....	88
Figure 4.4. Affect of standing time on the stability of SWNT dispersions and influence of PANi on stability of SWNT dispersion in (a) SWNT- DMPU (0.01 % w/w) (b) SWNT (0.01 % w/w)-PANi (0.01 % w/w) in DMPU. Photograph was taken 6 hr after sonication. Arrows indicate large agglomerates.....	89
Figure 4.5. Hydrodynamic diameter distribution of SWNTs in DMPU (0.01 % w/w) with (square) and without (inverted triangle) PANi. The distribution immediately after sonication is represented by filled symbols while the distribution measured 60 min after sonication was stopped is shown by unfilled symbols.	90
Figure 4.6. The size distribution of SWNTs bundle in DMPU for different concentrations of (Δ) 0.05 % w/w, (\square) 0.10 % w/w and (\square) 0.20 % w/w.....	91
Figure 4.7. Viscometry of SWNT (0.2 % w/w) in DMPU dispersions after different sonication times (a) 30 min, (b) 60 min and (c) 120 min.....	92

Figure 4.8. Variation of viscosity of spinning solution of PAni (LEB) 10% w/w in DMPU containing (a) 0.00 % (b) 0.05 % (c) 0.10 % or (d) 0.20 % (w/w) of SWNT with regard to solvent. Shear rate = 1 s^{-1}	93
Figure 4.9. Variation in viscosity of spinning solution based on PAni (LEB) 10 % w/w in DMPU containing (a) 0.00 % (b) 0.05 % (c) 0.10 % (d) 0.20 % (w/w) SWNT with regards to solvent, at different shear rates.....	95
Figure 4.10. Viscosity versus SWNTs content at different shear rate.....	97
Figure 4.11. Cross sectional SEMs of PAni (a, b) and PAni/SWNTs (2.0 % w/w SWNTs (c, d) into a coagulation baths containing (a,c) 10 % w/w NMP in water or (b, d) water using take up velocity of 2 m/min. Scale bar 30 μm	100
Figure 4.12. Cross sectional SEMs of PAni/SWNT fibres spun using different take up velocities for PAni(a, b) PAni/SWNTs containing 2 % w/w SWNT(c, d). Take up velocities were 3 m/min (a, c) or 6 m/min (b, d). Scale bar is 30 μm (a,c) and 10 μm (b, d).....	101
Figure 4.13. DSC thermal analysis curve of neat as spun polyaniline (LEB) fibre under a N ₂ atmosphere first cycle (thick line); second (reheat) cycle (thin line)	102
Figure 4.14. SEM micrographs of PAni/SWNTs fibres after thermal stretching containing (a) 0.0 %, (b) 0.5 %, (c) 1.0 % and (d) 2.0 % (w/w) SWNTs with respect to PAni.....	104
Figure 4.15. Stress strain curves of PAni/SWNTs composite fibres with varying SWNTs content, before doping (thick lines) and after doping for 24 hrs in MSA(thin	

lines). (a,a')Neat PANi, (b,b') PANi/SWNT (0.5 % w/w) (c,c') PANi/SWNT (1.0 % w/w) (d,d') PANi/SWNT(2.0 % w/w).....	106
Figure 4.16. SEM images showing a typical cross sectional surface of (a) neat PANi (b) PANi/ SWNT (2.0 % w/w).....	108
Figure 4.17. SEMs of PANi/SWNTs composite fibres under flexural load with SWNTs of (a) 0.0 % w/w (b) 0.5 % w/w(c) 1.0 % w/w (d) 2.0 % w/w.....	111
Figure 4.18. Enhanced Raman Spectra (before doping) of (a) neat SWNTs, (e) neat PANi and PANi/SWNTs fibres with varying SWNT content (b) 0.5 %w/w (c) 1.0% w/w, (d) 2.0% w/w ($\lambda_{exc}=632.8$).....	112
Figure 4.19. The schematic illustrating the interaction of SWNTs with PANi through the quinoid rings of latter.....	114
Figure 4.20. Enhanced Raman Spectra(after doping in MSA solution for 24 hrs following by drying at 100 °C) of (a) neat SWNTs (e) neat PANi and PANi/SWNTs with varying SWNTs content (b) 0.5 % w/w, (c) 1.0 % w/w, (d) 2.0 % w/w.....	115
Figure 4.21. The percolative behavior of SWNTs as filler in PANi matrix before doping	118
Figure 4.22. The Log-Log plot of conductivity vs reduced weight fraction of SWNTs.	118
Figure 4.23. The EPR spectra of PANi/SWNTs composite fibres before doping containing varying amounts of SWNTs. (a) 0.0 % w/w (b)0.5 %w/w, (c) 1.0 % w/w and (d) 2.0 % w/w.....	119

Figure 4.24. Cyclic voltametry of (a) neat PAni fibre (b) PAni/ SWNTs (2 % w/w) composite fibre. Scan rate= 50 mVs ⁻¹ , electrolyte: 1.0 M HCl (aq).....	123

Figure 5.1. First step of FIB milling: labeling of working area.....	134
Figure 5.2. Second step of FIB milling: (a) Pt deposition and (b) milling of sloping trenches.....	134
Figure 5.3. Third step: reduction of thickness of thin film.....	135
Figure 5.4. Fourth step of FIB milling: (a) Further thinning of the lamella and (b) cutting of holding edges.....	135
Figure 5.5. Final step of FIB milling: (a) transfer of the thin film on a TEM grid using a micro robot (b) Schematic indicating a micro robot machine.....	136
Figure 5.6. UV-Vis NIR spectra of SWNT (0.01 % w/w) in (a) DCAA after 30 min sonication (b) DCAA-AMPSA (2 % w/w) after 30 min sonication and (c) DMPU after 2 hrs sonication.....	141
Figure 5.7. Influence of AMPSA concentration (% w/w) in DCAA on hydrodynamic diameter distribution of SWNT dispersions (0.05 % w/w). (□) 0 % w/w (□)1 % w/w (□) 2 % w/w. The results were obtained 30 min after samples preparation.....	142
Figure 5.8. Hydrodynamic diameter of SWNTs (0.05 % w/w) in DCAA with (□) and without (□) AMPSA (2 % w/w). Hydrodynamic diameters immediately after sonication are indicated by the filled symbols; while those measured 60 min after sonication was stopped are indicated by the unfilled symbols.....	143

Figure 5.9. Influence of sonication time on homogeneity of SWNTs dispersion as gauged by fluctuation of viscosity versus shear rate. The dispersion contained 0.060 % w/w SWNT and 2 %w/w AMPSA relative to the DCAA solvent.	144
Figure 5.10. Average hydrodynamic diameter of SWNT dispersions for 5 repetitive experiments using either 10 min or 30 min sonication time. The dispersion contained 0.060 % w/w SWNT and 2 %w/w AMPSA relative to the DCAA solvent.....	145
Figure 5.11. Influence of SWNTs concentration in DCAA/AMPSA solution on hydrodynamic diameter (□) 0.030 %w/w (□) 0.045 %w/w (□) 0.060 %w/w (□) 0.090 %w/w.....	146
Figure 5.12. Viscosity vs. shear rate for SWNTs dispersion in DCAA containing 2 % w/w AMPSA for various SWNT loadings from 0.00% w/w to 0.09 % w/w.	147
Figure 5.13. Influence of SWNTs content on viscosity of PAni-ES/AMPSA/SWNT solution versus shear rate. The total concentration of PAni and AMPSA was 11.5 % w/w.....	149
Figure 5.14. Time before gelation indicated by sharp rise in viscosity for (a) neat PAni-ES/AMPSA and (b) PAni-ES/AMPSA/SWNT (0.090 % w/w) SWNT spinning solutions. Shear rate = 1 s ⁻¹	151
Figure 5.15. Typical SEM micrographs of as-spun fibres of (a) neat PAni-ES/AMPSA (b) PAni-ES/AMPSA/SWNT 0.76 %w/w.....	152

Figure 5.16. Typical SEM micrographs of 5x thermally stretched fibre of (a) PAni-ES/AMPSA (b) PAni-ES/AMPSA/SWNT (0.76 % w/w).scale bar is 10 μm	153
Figure 5.17. SEM micro graph of the PAni-ES/AMPSA/SWNT (0.76 %w/w)(a) side wall (b) cross section parallel to fibre axis.	154
Figure 5.18. TEM micrographs of thin film obtained by FIB milling, showing SWNTs dispersion within an PAni-ES/AMPSA matrix for (a) neat PAni-ESAMPSA (b) PAni-ES/AMPSA/SWNTs (0.76 %w/w SWNT.	155
Figure 5.19. The typical stress – strain curve of PAni-ES/AMPSA fibre and its composites with different SWNT contents (D fibre= $50\pm 20 \mu\text{m}$, strain rate= $500 \mu\text{m} / \text{min}$).	157
Figure 5.20. Strain recovery behavior of (□) neat PAni-ES/AMPSA fibre (□) PAni-ES/AMPSA/SWNT (0.76 % w/w) with cyclical application and removal of a 40 mN force.	158
Figure 5.21. SEM micrographs of full knots of (a) PAni-ES/AMPSA (b) PAni-ES/AMPSA/SWNT (0.76% w/w). SEM micrographs of 16 ply twisted fibre of PAni-ES/AMPSA/SWNT (0.76 % w/w) fibre with (c) S shaped twisting (d) Z shaped twisting. The number of twist per inch was 36.	159
Figure 5.22. (a)DSC thermogram of 5x drawn fibre (a) PAni-ES/AMPSA (b) PAni-ES/AMPSA/SWNT (0.76 %w/w). (b) The DSC thermogram for the first and second cycles of 5X drawn PAni-ES/AMPSA/SWNT.	161

Figure 5.23. (A) Storage modulus (B) the $\tan\delta$ (Loss modulus/Storage modulus) vs temperature curves for (a) PANi-ES/AMPSA and (b) PANi-ES/AMPSA - SWNTs (0.76 % w/w).....	163
Figure 5.24. Influence of SWNTs content on the electrical conductivity of PANi-ES/AMPSA/SWNTs fibres.....	164
Figure 5.25. log–log plot of electrical conductivity vs reduced mass fraction.....	165
Figure 5.26. Enhanced Raman spectra ($\lambda_{exc} = 632.8$ nm) obtained for PANi-ES/AMPSA/SWNTs obtained containing various amounts of SWNTs (a) 0.00 % w/w (b) 0.26 % w/w (c) 0.38 % w/w (d) 0.5 %w/w (e)0.76 % w/w and (f) SWNT bucky paper.....	167
Figure 5.27. Enhanced Raman spectra ($\lambda_{exc} =632.8$) of neat PANi-ES/AMPSA (a) before deprotonation, (b) 3 hr after deprotonation and (c) 6 hr after deprotonation (d) Raman spectrum of PANi(EB).Arrow indicates the transition from the protonated ES form to the deprotonated EB form.....	170
Figure 5.28. Enhanced Raman spectra ($\lambda_{exc}= 632.8$) of (a) Neat PANi-ES/AMPSA fibre before deprotonation, (b) Neat PANi-ES/AMPSA after 6 hrs deprotonation (c) PANi-ES/AMPSA/SWNT (0.76 % w/w) before deprotonation and (d) PANi-ES/AMPSA/SWNT (0.76 % w/w) after 24 hrs deprotonation.....	171
Figure 5.29. CV characterization of (a) PANi-ES/AMPSA fibre (b) PANi-ES/AMPSA /SWNTs fibre 0.76 % w/w (b) in 1.0 M HCl (aq) electrolyte. 10 th cycle shown for each CV. Scan rate 10 mV/s. (L=10 mm, D= 70 μ m).....	172
Figure 5.30. CV characterisation of fibres made of (a) PANi-ES/AMPSA/SWNT and (b) PANi-ES/AMPSA/SWNT (0.76 %w/w) in EMI.TFSI. potential cycled in	

range of (± 1.5), scan rate 50 mV/s, under 10 mN Load. (L=10 mm, D=70 μm).....175

Figure 5.31. Comparison of the electrochemical stability of (a,b) PAni-ES/AMPSA and (c,d) PAni-ES/AMPSA/SWNT (0.76 % w/w) over potential ranges of (a,c) ± 1.5 and ± 2 V (b,d).....177

Figure 5.32. CV characterisation of the PAni-ES/AMPSA/SWNT fibre illustrating electrochemical stability over 30 successive cycles. scan rate 50 mV/s, under 10 mN Load. Potential cycled in range of (± 2.0).....178

Figure 6.1. Demonstration of SWNTs coordination (xyz) in PAni-ES/AMPSA-SWNTs composite fibre (XYZ coordinates) and the fibre arrangement in reference frame of the Raman sample stage (x'y'z' coordinates).....187

Figure 6.2. The Raman spectra under VV and VH configuration, ψ = the angle between fibre axis and polarization plane (a) PAni-ES/AMPSA fibre (5x drawn fibre) for $\psi=0^\circ$ and 90° . VV configuration (b) PAni-ES/AMPSA-SWNT (0.76 % w/w) composite fibre (as spun) VV configuration (c) PAni-ES/AMPSA-SWNT (0.76 % w/w) composite fibre (5x drawn) VV configuration.(d) PAni-ES/AMPSA-SWNT (0.76 % w/w) composite fibre (5x) VH configuration. From top to bottom, the angle between fibre axis and polarization plane is 0° , 30° , 45° , 60° , 75° and 90°189

Figure 6.3. The Raman spectra under VV and VH configuration for RBM band, ψ = the angle between fibre axis and polarization plane (a) PAni-ES/AMPSA fibre

(5x drawn fibre) for $\psi=0^\circ$ and 90° . VV configuration (b) PAni-ES/AMPSA-SWNT (0.76 % w/w) composite fibre (5x) VH configuration	191
Figure 6.4. The comparison of $I_{vv}(\psi^\circ)/I_{vv} 0^\circ$ versus ψ in tangential mode (TM) and resonance breathing mode (RBM) modes for this work and references	192
Figure 6.5. The orientation distribution function of SWNT in PAni-ES/AMPSA-SWNT (0.76 %w/w) composite fibres constructed with the orientation parameters, $\langle P_2(\cos\theta) \rangle$ and $\langle P_4\cos(\theta) \rangle$ listed in Table 6.1	197
Figure 6.6. Effect of mechanical strain on the frequency shift of D* band of SWNTs incorporated in PAni-Es/AMPSA matrix. (dashed line) before applying strain (solid line) after applying 3 % strain.....	200
Figure 6.7. The Raman shift of D* peak of nanotube under axial tension for two sample of SWNT (0.76 %w/w) in the PAni.....	201
Figure 6.8. Mechanical versus spectroscopic stress – strain curve.....	202

Figure 7.1. Crystalline regions separated by disordered regions constitutes the heterogeneous morphology in composite fibre.....	209
Figure 7.2. The temperature dependence conductivity for PAni-ES/AMPSA fibre and their composite containing 0.25% and 0.76 %w/w SWNT.....	212
Figure 7.3. Log-Log plot of reduced activation energy (W) vs. temperature (\square) PAni-Es-AMPSA (Δ) PAni-Es-AMPSA-SWNT (0.25 % w/w) (\square) PAni-Es-AMPSA-SWNT (0.76 % w/w).....	213

Figure 7.4. The resistance arrangement in the proposed model of charge transport described in equation 7.1.....	215
Figure 7.5. The fitting quality of experimental data and proposed model and residual amount of least square of fitting calculation.....	219

Figure 8.1. Experimental set-up for actuation test in isotonic mode.....	232
Figure 8.2. Schematic shows the experimental set up used for measurement of resistance across the fibres for measurement of resistance in different humidity.....	236
Figure 8.3. The typical isotonic actuation data as a function of scanning potential in 1.0 M HCl at scan rate of 5 mV/s. Simultaneous demonstration of linear strain and cyclic voltammogram in one cycle for (a) Neat PANi-ES/AMPSA (b) PANi – ES/AMPSA/SWNT (0.76 % w/w)1 under 10 mN load.....	237
Figure 8.4. Isotonic strains measured during cyclic voltammetry in 1M HCl at 5 mV/s between -0.2 and 0.5V (vs. Ag/AgCl reference). Open and filled symbols show the results from two separate samples. Square symbols are for neat PANi-ES/AMPSA fibres and circles are for SWNT-reinforced fibre.....	239
Figure 8.5. Cyclic voltammograms showing current density (I) for potential (E) scans between -0.2V and +0.5V (vs. Ag/AgCl) in 1M HCl at 5 mV/s: a) neat PANi-ES/AMPSA and b) PANi-ES/AMPSA -SWNT fibres.....	242
Figure 8.6. Charge/discharge curves of PANi –ES/AMPSA or PANi-ES/AMPSA/SWNT (0.76 % w/w) fibres (a) PANi-ES/AMPSA fibre charges (b) PANi-ES/AMPSA fibre	

discharges(c) PANi –AMPSA-SWNT (0.76 % w/w) charges(d) PANi –ES/AMPSA-SWNT (0.76 % w/w) discharges.....244

Figure 8.7. Cycle life of (a) PANi-ES/AMPSA (b) PANi-ES/AMPSA/SWNT fibres...245

Figure8.8. The sensitivity of normalized resistivity versus (a) temperature by scan rate(3 °C/min) at constant humidity for (b)Neat PANi-ES/AMPSA (c) PANi-ES/AMPSA-SWNT.....247

Figure 8.9 (a) Pulse in relative humidity at constant temperature. The variation of normalised resistance(R/R0) for (b) PANi-ES/AMPSA fibre and (c) PANi-ES/AMPSA /SWNT composite versus humidity pulse change249

Figure 9.1. The comparison of tensile strength versus elongation at break of PANi –CNT fibre with commercial yarns.....261

Figure 9.2. The comparison of elastic modulus versus elongation at break of PANi –CNT fibre with commercial yarns.....261

LIST OF TABLES

Table 2.1. The solubility and conductivity of PANi cast from some typical protonic acids and solvents.....	26
Table 2.2. Different chirality based on chiral angle	29
Table 2.3. Typical mechanical properties of SWNTs compared with metals and carbon fibre.....	30
Table 2.4. The mechanical and electrical properties of SWNT in the form of bucky paper (mat) and fibres.....	32
Table 2.5. The mechanical and electrical properties of neat PANi fibre produced by the two step process.....	37
Table 2.6. The mechanical and electrical properties of PANi fibre processed from one step process.....	40
Table 2.7. The mechanical properties data of some synthetic and natural fibre	41
Table 2.8. The electrical and mechanical properties of composite of PANi and thermoplastic polymer.....	42

Table 3.1. Viscosity ranges and spindles.....	60

Table 4.1. Formulation of PANi (LEB)/SWNT-DMPU composite spinning solutions	81
Table.4.2. Elemental analysis of purified SWNTs prepared by Hipco@CNI(PO257).....	84

Table 4.3. Vibrational modes observed for Raman scattering in SWNTs	85
Table 4.4. Electronic transitions reported for dispersed SWNTs and their occurrence in different solvents.....	87
Table 4.5. Power law coefficients and exponents for PANi solution with different SWNT content in DMPU.....	96
Table 4.6. The typical diameters, deniers and densities of thermally stretched 2x drawn PANi/SWNT fibre containing different amounts of SWNTs.....	105
Table 4.7. Influence of SWNTs loading on mechanical properties of PANi/SWNTs fibres before acid doping.....	107
Table 4.8. Influence of SWNTs loading on mechanical properties of PANi/SWNT fibres after doping with MSA for 24 hr.....	107
Table 4.9. The effective elastic modulus of SWNT bundles embedded in undoped and doped PANi matrix.....	110
Table 4.10. Assignment of enhanced Raman spectra bands.....	113
Table 4.11. Influence of drying temperature on four point probe conductivity of 2x PANi/SWNTs fibres (2X) with varying SWNT content after acid doiping	120

Table 5.1. Range of PANi and AMPSA contents used to prepare PANi-ES/AMPSA solutions in DCAA for fibre spinning. 20 g of DCAA was used for each.	137

Table 5.2. Amount of PANi (EB), AMPSA and SWNTs used for the preparation of PANi-ES/AMPS/SWNTs spinning solution (each solution made up in 20 g DCAA solvent).....	138
Table 5.3. Summary of observations made during attempts to spin fibres from mixures “S1” to “S4”(refer Table 5.1).....	148
Table 5.4. The power law index and consistency index for samples containing different amounts of SWNTs.....	150
Table 5.5. The mechanical properties of PANi-ES/AMPSA fibre and its composites with different SWNT contents.....	157
Table 5.6. The influence of SWNT loading on four point probe conductivity of 5xdrawn fibre of PANi/AMPSA.....	165
Table 5.7. The assigned frequencies originated from PANi-ES/AMPSA and its SWNTs composite.....	168
Table 5.8. The chemical structure of the ionic liquids 1-butyl-3-methyl imidazolium tetrafluoroborate (BMI.BF ₄) and ethyl methyl imidazolium bis (trifluoro methane sulfonyl) imide (EMI.TFSI).....	174

Table 6.1. The polarized Raman scattering intensity ratio of TM and RBM bands in VV configuration ($\theta=0^\circ, 90^\circ$) versus VH configuration at $\theta=0^\circ$ for as-spun and 5x drawn fibres of PANi-Es/AMPSA-SWNT (0.76 % w/w). Orientation order parameters are listed for construction of orientation distribution function....	196
---	-----

Table 6.2. The comparison of predicted elastic modulus from rule of mixture and experimental value.....199

Table 7.1. The conductivity parameters for PANi-ES/AMPSA fibre and its SWNT composite fibre.....214

Table 7.2. The sensitivity of the model to the initial starting values for the fitting.....217

Table 7.3. The fitting parameters presented in equation 7.2 for different samples.....220

Table 7.4. The contribution of metallic resistivity in bulk resistivity and the metallic disorder in amorphous resistivity.....221

Table 8.1. The description of aqueous solution required for preparation of different relative humidity in the conductivity chamber.....235

Table 8.2. Measured and calculated properties of PANi-ES/AMPSA-SWNT fibre composites.....241

Table 9.1. The comparison of one step and two steps methods by considering economical and safety issues.....266

Table 9.2. The hazardous identification of non similar material used in one step and two steps methods.....267

LIST OF SCHEME

Scheme 1.1. The schematic of the selection of conducting polymers.....	3

Scheme 2.1. (a)A general scheme for polymerisation of Aniline (b) different oxidation state of PANi	18
Scheme 2.2. Interconversions between different forms of polyaniline	19
Scheme 2.4. The chemical structure of DMPU and NMP.....	21
Scheme 2.5. Hydrogen bonding between PANi (EB) to DMPU.....	21
Scheme 2.6. The interaction of LEB chain with carbonyl group of DMPU.....	23
Scheme 2.7. Some of sulfonic acid dopants used for one step PANi fibre processing.....	25

Scheme 5.1. Polaronic (semiquinoid), bipolaronic and oxidized unit of PANi.....	169
Scheme 5.2. The mechanism of electrochemical switching of PANi-ES/AMPSA between ES-LEB oxidation states in EMI.TFSA.....	176