University of Wollongong

Research Online

Australian Institute for Innovative Materials -
Papers

Australian Institute for Innovative Materials

2012

Magnetic and superconducting properties of spin-fluctuation-limited superconducting nanoscale VN_x

R Zeng

University of Wollongong, rzeng@uow.edu.au

J Liu

University of Wollongong, jliakunl@uow.edu.au

G Du

University of Western Sydney

W. X. Li

University of Wollongong, wenxian@uow.edu.au

J Wang

University of Wollongong

See next page for additional authors

Follow this and additional works at: <https://ro.uow.edu.au/aiimpapers>

Part of the [Engineering Commons](#), and the [Physical Sciences and Mathematics Commons](#)

Research Online is the open access institutional repository for the University of Wollongong. For further information contact the UOW Library: research-pubs@uow.edu.au

Magnetic and superconducting properties of spin-fluctuation-limited superconducting nanoscale VN_x

Abstract

"VN_x nanoparticles and nanowires have been prepared by nitrifying V₂O₅ nanoparticles (NP) and nanowires (NW). The V₂O₅ NP and NW were synthesized by a facile hydrothermal method. Magnetic susceptibility (χ) and magnetization measurements showed long range superconducting ordering (LRSO) at the temperature of 5.8 K for NW, but there was no observation of LRSO (at least down to 2 K) for the NP sample, which is a much lower temperature than for the corresponding bulk, while both NP and NW showed the absence of long range magnetic ordering, at least down to 2 K. However, the χ data showed that both samples possess a high Pauli-like component, $\chi(0)$, in their susceptibility ($\chi(0)$ approximate to 2.22×10^{-4} emu/mol for NP and 5×10^{-4} emu/mol for NW). Moreover, for the NW samples, χ has a strong magnetic field dependence and presents a non-linear field-polarization feature, suggesting strong spin-orbit coupling. (C) 2012 American Institute of Physics. [doi:10.1063/1.3679148]"

Keywords

superconducting, properties, spin, fluctuation, limited, nanoscale, magnetic, vn_x

Disciplines

Engineering | Physical Sciences and Mathematics

Publication Details

Zeng, R., Liu, J., Du, G., Li, W., Wang, J., Horvat, J. & Dou, S. X. (2012). Magnetic and superconducting properties of spin-fluctuation-limited superconducting nanoscale VN_x. *Journal of Applied Physics*, 111 (7), 07E142-1-07E142-4.

Authors

R Zeng, J Liu, G Du, W. X. Li, J Wang, J Horvat, and S X. Dou

Magnetic and superconducting properties of spin-fluctuation-limited superconducting nanoscale VN_x

R. Zeng, J. Liu, G. D. Du, W. X. Li, J. L. Wang et al.

Citation: *J. Appl. Phys.* **111**, 07E142 (2012); doi: 10.1063/1.3679148

View online: <http://dx.doi.org/10.1063/1.3679148>

View Table of Contents: <http://jap.aip.org/resource/1/JAPIAU/v111/i7>

Published by the [American Institute of Physics](#).

Related Articles

Near-field radiative heat transfer between doped silicon nanowire arrays

Appl. Phys. Lett. **102**, 053101 (2013)

Red-green-blue light sensitivity of oxide nanowire transistors for transparent display applications

AIP Advances **3**, 012112 (2013)

Manganese nanoclusters and MnSi_{1.7} nanowires formed on Si(110): A comparative x-ray photoelectron spectroscopy study

J. Appl. Phys. **113**, 024305 (2013)

Directional-dependent coercivities and magnetization reversal mechanisms in fourfold ferromagnetic systems of varying sizes

J. Appl. Phys. **113**, 013901 (2013)

Critical shell thickness for InAs-AlxIn_{1-x}As(P) core-shell nanowires

J. Appl. Phys. **112**, 124305 (2012)

Additional information on J. Appl. Phys.

Journal Homepage: <http://jap.aip.org/>

Journal Information: http://jap.aip.org/about/about_the_journal

Top downloads: http://jap.aip.org/features/most_downloaded

Information for Authors: <http://jap.aip.org/authors>

ADVERTISEMENT

The advertisement banner for AIP Advances features a green and yellow background with abstract wavy lines. The AIP Advances logo is prominently displayed in the center, with the text 'AIPAdvances' in a green font. To the right, a circular seal states 'Now Indexed in Thomson Reuters Databases'. Below the logo, the text 'Explore AIP's open access journal:' is followed by a list of three bullet points: 'Rapid publication', 'Article-level metrics', and 'Post-publication rating and commenting'.

AIPAdvances

Now Indexed in
Thomson Reuters
Databases

Explore AIP's open access journal:

- Rapid publication
- Article-level metrics
- Post-publication rating and commenting

Magnetic and superconducting properties of spin-fluctuation-limited superconducting nanoscale VN_x

R. Zeng,^{a)} J. Liu, G. D. Du, W. X. Li, J. L. Wang, J. Horvat, and S. X. Dou

Institute for Superconducting and Electronic Materials, University of Wollongong, NSW 2522, Australia

(Presented 3 November 2011; received 11 October 2011; accepted 4 December 2011; published online 12 March 2012)

VN_x nanoparticles and nanowires have been prepared by nitrifying V₂O₅ nanoparticles (NP) and nanowires (NW). The V₂O₅ NP and NW were synthesized by a facile hydrothermal method. Magnetic susceptibility (χ) and magnetization measurements showed long range superconducting ordering (LRSO) at the temperature of 5.8 K for NW, but there was no observation of LRSO (at least down to 2 K) for the NP sample, which is a much lower temperature than for the corresponding bulk, while both NP and NW showed the absence of long range magnetic ordering, at least down to 2 K. However, the χ data showed that both samples possess a high Pauli-like component, χ_0 , in their susceptibility ($\chi_0 \approx 2.22 \times 10^{-4}$ emu/mol for NP and 5×10^{-4} emu/mol for NW). Moreover, for the NW samples, χ has a strong magnetic field dependence and presents a non-linear field-polarization feature, suggesting strong spin-orbit coupling. © 2012 American Institute of Physics. [doi:10.1063/1.3679148]

The study of nanoscale superconductivity has attracted much attention recently, because it involves such fundamental phenomena as macroscopic quantum tunneling, quantum phase transitions, and environmental effects, and because it has such significant potential applications in electronics circles and quantum computing.^{1–12} One of the key issues is the effect of quantum fluctuations on the dynamic behavior of ultra-small superconductors with dimensions much less than the temperature-dependent coherence length, $\xi(T)$.^{1,2} Of special interest from both the fundamental and the practical points of view are the dynamical processes of switching between the superconducting and paramagnetic states in the presence of a magnetic field. Small grains can experience spontaneous transitions due to quantum fluctuations. Although experimental studies have been made on a few superconductors, such as MoGe,^{1,5} Pb,² Nb,⁵ Al,^{10,11} Sn,¹² and even high temperature superconducting (SC) nanowires¹³ in recent years, there are still controversies on what the expected properties of a one-dimensional (1D) superconductor are. For the VN_x superconductors, one more interesting feature is their spin fluctuation limited superconductivity, which make the superconducting transition temperature $T_c < 10$ K, much lower than the theoretically predicted ~ 30 K.^{14–16}

Achieving fully stoichiometric VN_x with the NaCl structure is a difficult proposition. This is because the superconducting transition temperature (T_c) has a linear relationship with the x value.¹⁵ Single-phase samples have only been successfully prepared with x up to 0.93 and T_c up to 9.8 K.¹⁴ The N vacancies have dominated the SC T_c and other SC properties, and should significantly influence the magnetic properties as well. The x can be determined from x-ray diffraction (XRD) through the lattice parameter and T_c measurement results due to the linear variation of T_c with x .¹⁵ To the best of our knowledge, there has been no report yet on the magnetic and superconducting properties of nano-scaled VN_x.

VN_x nanoparticle (NP) and nanowire (NW) samples were prepared by nitrifying long V₂O₅ nanoparticles and nanowires, which had been synthesized by a facile hydrothermal method that will be reported elsewhere.

The XRD patterns of the (220) peak are shown in Fig. 1(a). Analysis indicated that all diffraction peaks can be indexed to a cubic cell with lattice constants $a = b = c = 4.112$ Å for the NP sample and $a = b = c = 4.138$ Å for the NW sample, confirming that the crystal structure of the VN_x belongs to the typical NaCl structure. The lattice parameter of both samples is smaller than that of fully stoichiometric VN_x ($x = 1$) due to N element vacancies. According to the relationship between x and the lattice parameter,^{15,16} we can calculate that $x \approx 0.86$ for NP and $x \approx 0.93$ for NW. The morphology of the VN_x samples was investigated by SEM, as shown in Fig. 1(b) for NP and Fig. 1(c) for NW. The NP sample clearly has nanoparticles with diameters of 6–10 nm, and the NW sample is shown to have a diameter of 30–80 nm with a length of a few micrometers. The nanoscale structure generates high surface area, and de-confined free electrons and delocalized spins may appear, so that it would exhibit unique magnetic properties.¹⁷

The FC χ - T curve of the NP sample is also shown in the inset of Fig. 2(a). The results show that the superconducting transition temperature $T_c = 5.8$ K for the NW sample, which is lower than the supposed T_c , while the superconducting transition cannot be observed for the NP sample down to 2 K. We also plotted the χT - T curves (Fig. 2(c)) for both the NP and NW samples under different fields and note that the curves show linearly T -dependent Pauli-like susceptibility over the $T > T_c$ temperature range (6–300 K). This is because the χ - T curve can be fit quite well using the sum of a Curie-like susceptibility, χ_C , and a linearly T -dependent Pauli-like susceptibility, χ_P ,

$$\chi = \chi_C + \chi_P = [C_{CW}/(T + \Theta_{CW})] + [\chi_0 + \chi_1 T], \quad (1)$$

where $\chi_0 = 4.13 \times 10^{-4}$ emu/mol; $\chi_1 = -1.68 \times 10^{-7}$ emu/mol K; the Curie-Weiss temperature, $\Theta_{CW} = 12.8$ K; and the Curie constant, $C_{CW} = 0.0323$ emu/mol, e.g., the effective localized

^{a)}Author to whom correspondence should be addressed. Electronic mail: rzeng@uow.edu.au.

FIG. 1. (Color online) (a) X-ray diffraction patterns of the VN_x nanoparticles (black symbols) and nanowires (blue symbols). The inset is the pattern of the (220) peaks; the blue dot-dashed lines indicate the (220) peak position of each sample. SEM images of the VN_x (b) nanoparticles and (c) nanowires.

magnetic moment, $\mu_{\text{eff}}^{\text{Local}} = 0.51 \mu_B$ for the NW sample. With similar fitting for the NP sample, we obtained that: $\chi_0 = 2.22 \times 10^{-4}$ emu/mol; $\chi_1 = -1.13 \times 10^{-7}$ emu/mol K; the Curie-Weiss temperature, $\Theta_{\text{CW}} = -0.39$ K; and the Curie constant, $C_{\text{CW}} = 0.00455$ emu/mol, e.g., $\mu_{\text{eff}}^{\text{Local}} = 0.19 \mu_B$. Selected susceptibility χ - T and χT - T curves under different fields are shown in Figs. 2(b) and 2(c), and the fitting results are plotted in Fig. 2(d).

The above fittings indicate that this system presents unusual spin features for the NW sample: (i) There is a large, bare Pauli-like susceptibility $\chi_0 = 4.13 \times 10^{-4}$ emu/mol, but a small effective magnetic moment ($\mu_{\text{eff}} = 0.67 \mu_B$), which is much smaller than that of the molecular field theoretical value for spin only ($J=S$). The V^{2+} ion local spin moment of $\mu_{\text{eff}}^{J=S} = [4S(S+1)]^{1/2} = 3.87 \mu_B$ ($S=3/2$ for the V^{2+} ion), but this is close to the moment of considering the spin-orbit coupling, $\mu_{\text{eff}}^{J=L \pm S} = g_J[J(J+1)]^{1/2} = 0.77 \mu_B$. g_J is the Lande g factor, while S and L are the spin and orbital quantum numbers, respectively, which suggests that the system has strong spin-orbit coupling. (ii) However, as shown in the inset of Fig. 2(c), the Pauli-like susceptibility contributes strong field dependence, such that χ_0 is changed from 4.13×10^{-4} emu/mol under a field of 1000 Oe to

FIG. 2. (Color online) (a) Semi-log plots of χ - T curves under zero field cooling (ZFC: black symbol line) and field cooling (FC: red symbol line) in an external magnetic field $H=1$ kOe, with the blue dot-dashed line the Curie-Weiss fitting line according to Eq. (1) in the text. The inset is the χ - T curve under an applied 1 K Oe field for the nanoparticle sample, with the blue dot-dashed line representing the $\chi \propto -\log(T)$ relationship. (b) Semi-log plots of χ - T curves under the indicated applied fields, with the inset showing an enlargement of the temperature region around T_c . (c) Semi-log plots of χ - T curves under the indicated applied fields; the inset contains normal plots of the χT - T curves, with the blue dot-dashed line representing the $\chi T \propto \log(T)$ relationship line. (d) Plots of susceptibility fitting results with field.

3.37×10^{-4} emu/mol under a field of 110 kOe. Similarly, the effective moment is reduced from $\mu_{\text{eff}} = 0.67 \mu_B$ to $0.34 \mu_B$, which presents a non-linear field-polarization feature, and suggests that the nanostructure with high surface area and high density of defects has delocalized a great amount of electrons, while at the same time, the nanowire 1D structure has confined the electrons, with magnetic field strongly inducing the polarization of free electron spins and spins being localized by strong spin-orbital coupling.

Our susceptibility analysis supports the conjecture that spin-liquid-like behavior may emerge from this system. When the temperature $T_c < T < 38$ K (100 Oe), $\chi \propto -\log(T)$ (as shown in Fig. 2(b)), or $\chi T \propto \log(T)$ (as shown in Fig. 2(c)), indicating a linear relationship with the log of the temperature, and all the straight lines under different applied fields are nearly parallel to one another, with the field only slightly changing the slopes of the lines.

A series of isothermal magnetization (M - H) loops between 2.1 and 305 K under fields up to 9 T has been collected for the NW sample, as shown in Fig. 3. The results include: (a) M - H curves for $T > T_c$, (b) M - H curves at temperature $T <$ and near T_c , (c) decomposition of M - H loops at $T <$ and near T_c , and (d) critical field H_c - T diagram. It is interesting that, at 305 K, the loop shows ferromagnetic-like (FM-like) behavior, which is more clearly shown in the inset of Fig. 3(a), containing the loops after subtraction of the Pauli-like component. Following the suggestion from Eq. (2) that the system can be described in terms of the sum of contributions from the Pauli- and Curie-like terms, we fit the 305 K magnetization experimental data to:

$$M(H) = M_{\text{Pauli}}(H) + M_{\text{Curie}}(H) \\ = \chi * \times H + M_0 B\{S^T, H, T\}. \quad (2)$$

FIG. 3. (Color online) (a) Selected isothermal M - H loops ($\mu_0 H < 0.5$ T) for VN_x nanoparticles at 8 K, 80 K, 200 K, and 305 K, respectively; the inset shows the loops after subtraction of the linear Pauli-like component. (b) M - H loops for VN_x nanoparticles at 8 K, 6 K, 4 K, and 2 K, respectively; the inset shows the enlarged loops for determining the lower critical field, H_{c1} . (c) Spin fluctuation subtracted (superconducting contribution only) isothermal M - H loops for VN_x nanoparticles at 2 K, 4 K, 6 K, 8 K, and 305 K, respectively; the insets show the straight linear Pauli-component of the loops (right) and the Curie component of the loops with the Pauli-component subtracted (left). (d) Upper critical field H_{c2} - T curve determined from the χ - T and M - H curves, with the superconducting critical current density (J_c) related ΔM - H curves at 2 K and 4 K presented in the inset.

The results can be fitted with the dominant contribution $\chi^* = 2.14 \times 10^{-4} \text{ emu mol}^{-1} \text{ Oe}^{-1}$, $B\{S^T, H, T\}$ is the Brillouin function, S^T is the Stone factor, and $M_0 = 5.27 \times 10^{-3} \mu_B/\text{f.u.}$. The behavior of $B\{S^T, H, T\}$ for $H < 5 \text{ kOe}$ is more typical of a superparamagnet, with $S^T \approx 15$. The value of M_0 corresponds to $5.27 \times 10^{-3} \mu_B/\text{f.u.}$, suggesting that only a small number of spins contribute to the second term in Eq. (3). The non-linear low-field magnetization and Curie-like susceptibility seem to arise from a relatively small number of FM spin clusters with $5.27 \times 10^{-3} \mu_B/\text{f.u.}$ and $S^T = 15$. When this is subtracted from $M(H)$ and $\chi^*(T)$, we are left with the intrinsic susceptibility of this 1D system, characterized by a still very large $\chi^* = \delta M / \delta H = 2.14 \times 10^{-4} \text{ emu mol}^{-1} \text{ Oe}^{-1}$. Similarly, by fitting the M - H loops for temperatures from 6 to 305 K, we obtained that (i) for $305 \text{ K} > T > 120 \text{ K}$, the M_0 , $S^T = 15$, and χ^* remain nearly constant; (ii) for $120 \text{ K} > T > 38 \text{ K}$, the low field M_0 and S^T decrease and χ^* increases with decreasing temperature; an M_0^* that is polarized in high field appears in this system, and the high-field M_0^* increases with decreasing T ; (iii) for $38 \text{ K} > T > 6 \text{ K}$, the low field M_0 disappears, and the high field M_0^* , S^T , and χ^* increase with decreasing T .

From analysis of the M - H loops at temperatures near and below T_c , as shown in Fig. 2(b), it was found that there is an electron Cooper pair interaction (superconducting state) component added to the system, so that Eq. (2) was modified to the following Eq. (3):

$$M(H) = M_{\text{Spin}}(H) + M_{\text{SC}}(H) \\ = \chi^* \times H + M_0 B\{S^T, H, T\} + M_{\text{SC}}(H) \quad (3)$$

where the $M_{\text{Spin}}(H)$ is the spin fluctuation contribution, and $M_{\text{SC}}(H)$ is the superconducting Cooper pair contribution. We conducted the fitting and subtraction of M - H curves as shown in Fig. 2(b); the $M_{\text{SC}}(H)$ component is shown in Fig. 2(c), with the $M_{\text{Curie}}(H)$ and the $M_{\text{Pauli}}(H)$ components shown in the right and left insets of Fig. 2(c), respectively. From the $M_{\text{SC}}(H)$ - H loop, we can evaluate the superconducting critical current density J_c , with J_c corresponding to the area of ΔM . The magnetic J_c was derived from the height of the magnetization loop ΔM using the Bean model: $J_c = 15 \Delta M / [\pi a^2 h]$, where a and h are the radius and length of a typical grain in the wire sample. From the superconducting transition temperature point under different fields and the convergence point of the $M_{\text{SC}}(H)$ - H loop (as shown in Fig. 3(b)), we can determine the upper field H_{c2} - T curve, which is plotted in Fig. 3(d), and the ΔM - H curves at 4 K and 2 K, which correspond to the J_c , because it is very hard to determine the size of grains in the nanowire sample, are plotted in the inset of Fig. 3(d). The J_c - H curves correspond to the ΔM - H curves at different temperatures, and the H_{c2} - T curve presents normal superconducting features, although the H_{c2} is lower than for the corresponding bulk.^{14–16}

It is interesting to notice that coexistence and competition effects of the superconducting Cooper pairs and of the Pauli and field-polarized electrons (Figs. 3(b) and 3(c)) are present in the system, which has motivated us to conjecture the electron pairing and breaking mechanism. Spin fluctuation had been predicted¹⁸ to exhibit strong effects in VN, which are characterized by a Stoner factor, S^T , greater than 1,

$$S^T = (\chi - \chi_{\text{Orb}}) / \chi_{\text{Pauli}}, \quad (4)$$

where χ is the susceptibility, χ_{Orb} is the orbital susceptibility, and S^T represents the exchange enhancement of the non-orbital spin part above the ordinary Pauli term, χ_{Pauli} . The Pauli-like conduction electrons and electron-phonon coupling are the necessary conditions for the formation of Cooper pairs, which are involved in the spin-orbit coupling in the VN nanowire system. Under lower field, the χ_{Pauli} is very large (Fig. 1(d)), and there are even local FM spin clusters. One of the important superconductivity mechanisms of high T_c cuprate superconductors is that the Cooper pairs form in a spin liquid induced by antiferromagnetic fluctuations, and this indicates that the emergence of spin liquid behavior is beneficial for the formation of pairs.¹⁹ It has long been known that magnetic fields suppress superconductivity through two main effects: first, by aligning the electron spins (i.e., the Zeeman effect) and second, by raising the kinetic energy of electrons via Meissner screening currents (i.e., the orbital effect).²⁰ For VN, both effects occur to suppress the T_c , due to strong spin-fluctuation, e.g., Eq. (4) effects. Moreover, in nanosized VN_x , the N vacancies tend to decrease the T_c , while nanosized quantum effects further decrease the T_c , as we obtained $x \approx 0.86$ for NP and $x \approx 0.936$ for NW from the XRD results. These values suggest that T_c should be 4.2 K for NP and 8.5 K for NW, much higher than the measured $< 2 \text{ K}$ for NP and 5.7 K for NW.

In summary, the magnetic behavior and the superconducting properties in VN_x nanoparticles (NP) and nanowires (NW) have been investigated by magnetic measurements. The NP sample with $x = 0.86$ exhibits the absence of any long-range spin or superconducting ordering, while the NW sample with $x = 0.93$ exhibits long-range superconducting ordering at 5.8 K. Susceptibility measurements indicated that the VN_x possesses a very high Pauli-like component and suggest that the system exists in a highly spin disordered state. The superconducting ordering suppressed by the N content x , and the particle size and shape, is further suppressed by the strong spin-fluctuation.

The authors thank Dr. T. Silver for her help and useful discussions. This work is supported by the Australian Research Council through a Discovery project (project ID: DP0879070).

¹A. Bezryadin, C. N. Lau, and M. Tinkham, *Nature* **404**, 971 (2000).

²Y. Guo, Y. F. Zhang, *et al.* *Science* **306**, 1915 (2004).

³K. A. Matveev, A. I. Larkin, *et al.* *Phys. Rev. Lett.* **89**, 096802 (2002).

⁴J. Wang, M. Singh, *et al.* *Nat. Phys.* **6**, 389 (2010).

⁵A. Rogachev and A. Bezryadin, *Appl. Phys. Lett.* **83**, 512 (2003).

⁶J. P. Cleuziou, W. Wernsdorfer, *et al.* *Nat. Nanotechnol.* **1**, 53 (2006).

⁷K. Y. Arutyunov, *Phys. Rep.* **464**, 1 (2008).

⁸L. Chirrolli and G. Burkard, *Phys. Rev. B* **74**, 174510 (2006).

⁹J. G. Wang, M. L. Tian, *et al.* *Nano Lett.* **5**, 1247 (2005).

¹⁰M. Zgirski, K.-P. Riikonen, *et al.* *Nano Lett.* **5**, 1029 (2005).

¹¹F. Altomare, A. M. Chang, *et al.* *Phys. Rev. Lett.* **97**, 017001 (2006).

¹²M. Tian, J. Wang, *et al.* *Appl. Phys. Lett.* **83**, 1620 (2003).

¹³K. Xu and J. R. Heath, *Nano Lett.* **8**, 3845 (2008).

¹⁴K. E. Gray, R. T. Kampwirth, *et al.* *Phys. Rev. B* **38**, 2333 (1988).

¹⁵F. I. Ajami and R. K. MacCrone, *J. Phys. Chem. Solids* **36**, 7 (1975).

¹⁶H. L. Luo, S. A. Wolf, *et al.* *Phys. Rev. B* **29**, 1443 (1984).

¹⁷J. Liu, *et al.* *Chem. Commun.* **46**, 3887 (2010).

¹⁸H. Rietschel, H. Winter, *et al.* *Phys. Rev. B* **22**, 4284 (1980).

¹⁹P. A. Lee, *et al.* *Rev. Mod. Phys.* **78**, 17 (2006).

²⁰M. Tinkham, *Introduction to Superconductivity*, 2nd ed. (McGraw-Hill, New York, 1996).