

University of Wollongong

Research Online

---

Australian Institute for Innovative Materials -  
Papers

Australian Institute for Innovative Materials

---

1-1-2013

## 'Laser chemistry' synthesis, physicochemical properties, and chemical processing of nanostructured carbon foams

Andres Seral-Ascaso  
*Instituto de Carboquímica ICB-CSIC*

Rosa Garriga  
*University of Zaragoza*

Maria Luisa Sanjuan  
*University of Zaragoza*

Joselito M. Razal  
*University of Wollongong, jrazal@uow.edu.au*

Ruth Lahoz  
*University of Zaragoza*

*See next page for additional authors*

Follow this and additional works at: <https://ro.uow.edu.au/aiimpapers>



Part of the [Engineering Commons](#), and the [Physical Sciences and Mathematics Commons](#)

---

Research Online is the open access institutional repository for the University of Wollongong. For further information contact the UOW Library: [research-pubs@uow.edu.au](mailto:research-pubs@uow.edu.au)

---

# 'Laser chemistry' synthesis, physicochemical properties, and chemical processing of nanostructured carbon foams

## Abstract

Laser ablation of selected coordination complexes can lead to the production of metal-carbon hybrid materials, whose composition and structure can be tailored by suitably choosing the chemical composition of the irradiated targets. This 'laser chemistry' approach, initially applied by our group to the synthesis of P-containing nanostructured carbon foams (NCFs) from triphenylphosphine-based Au and Cu compounds, is broadened in this study to the production of other metal-NCFs and P-free NCFs. Thus, our results show that P-free coordination compounds and commercial organic precursors can act as efficient carbon source for the growth of NCFs. Physicochemical characterization reveals that NCFs are low-density mesoporous materials with relatively low specific surface areas and thermally stable in air up to around 600 degrees C. Moreover, NCFs disperse well in a variety of solvents and can be successfully chemically processed to enable their handling and provide NCF-containing biocomposite fibers by a wet-chemical spinning process. These promising results may open new and interesting avenues toward the use of NCFs for technological applications.

## Keywords

physicochemical, processing, synthesis, carbon, chemistry, nanostructured, laser, chemical, properties, foams

## Disciplines

Engineering | Physical Sciences and Mathematics

## Publication Details

Seral-Ascaso, A., Garriga, R., Luisa Sanjuan, M., Razal, J. M., Lahoz, R., Laguna, M., De La Fuente, G. F. & Munoz, E. (2013). 'Laser chemistry' synthesis, physicochemical properties, and chemical processing of nanostructured carbon foams. *Nanoscale Research Letters*, 8 (1 (233)), 1-6.

## Authors

Andres Seral-Ascaso, Rosa Garriga, Maria Luisa Sanjuan, Joselito M. Razal, Ruth Lahoz, Mariano Laguna, German F. De La Fuente, and Edgar Munoz

**NANO EXPRESS**

**Open Access**

# 'Laser chemistry' synthesis, physicochemical properties, and chemical processing of nanostructured carbon foams

Andrés Seral-Ascaso<sup>1</sup>, Rosa Garriga<sup>2</sup>, María Luisa Sanjuán<sup>3</sup>, Joselito M Razal<sup>4</sup>, Ruth Lahoz<sup>3</sup>, Mariano Laguna<sup>5</sup>, Germán F de la Fuente<sup>3</sup> and Edgar Muñoz<sup>1\*</sup>

## Abstract

Laser ablation of selected coordination complexes can lead to the production of metal-carbon hybrid materials, whose composition and structure can be tailored by suitably choosing the chemical composition of the irradiated targets. This 'laser chemistry' approach, initially applied by our group to the synthesis of P-containing nanostructured carbon foams (NCFs) from triphenylphosphine-based Au and Cu compounds, is broadened in this study to the production of other metal-NCFs and P-free NCFs. Thus, our results show that P-free coordination compounds and commercial organic precursors can act as efficient carbon source for the growth of NCFs. Physicochemical characterization reveals that NCFs are low-density mesoporous materials with relatively low specific surface areas and thermally stable in air up to around 600°C. Moreover, NCFs disperse well in a variety of solvents and can be successfully chemically processed to enable their handling and provide NCF-containing biocomposite fibers by a wet-chemical spinning process. These promising results may open new and interesting avenues toward the use of NCFs for technological applications.

**Keywords:** Carbon nanostructures, Laser ablation, Metal-carbon hybrids, Laser chemistry, Metal nanoparticles, Fiber spinning

## Background


Laser technologies can be successfully utilized for the production of carbon-nanostructured materials exhibiting fascinating structural and physical properties such as carbon nanotubes [1], carbon nanohorns [2], carbon nanofoams [3], or shell-shaped carbon nanoparticles [4]. Our group discovered the production of metal-nanostructured foams (NCFs) by laser ablation of triphenylphosphine (PPh<sub>3</sub>)-containing organometallic targets [5]. We then demonstrated that organic ligands can act as efficient carbon sources for the laser ablation production of carbon nanomaterials. Metal-NCFs are three-component materials which consist of amorphous carbon aggregates, metal nanoparticles embedded in amorphous carbon matrices, and graphitic nanostructures. The metal-NCF composition, metal nanoparticle size, and dilution (i.e., metal and carbon

content) within the carbon matrices can be tailored by conveniently choosing the metals (Au, Cu) and ligands of the ablated targets [6]. On the other hand, laser ablation of PPh<sub>3</sub> resulted in the production of metal-free NCFs consisting of graphitic nanostructures and P-containing amorphous carbon aggregates [6]. We report how our versatile 'laser chemistry' approach can be extended to the synthesis of a variety of other metal-NCFs, as well as to metal-free, P-free NCFs, proving that the synthesis of NCFs is not restricted to PPh<sub>3</sub>-based targets and therefore enabling envisioning the synthesis of metal-carbon hybrids by chemical design. Additionally, physicochemical studies have been performed on metal-free NCFs to evaluate their potential applications. We also show that NCFs can be easily chemically processed in the form of stable NCF dispersions in different solvents and NCF biocomposite fibers, which offer promise for NCF incorporation into different matrices and technological applications.

\* Correspondence: edgar@icb.csic.es

<sup>1</sup>Instituto de Carboquímica ICB-CSIC, Miguel Luesma Castán 4, 50018 Zaragoza, Spain

Full list of author information is available at the end of the article




## Methods


The production of carbon foams has been carried out by Nd:YAG laser ablation of thick layers of coordination and organic compounds in air atmosphere using the setup described in Figure 1 and under the experimental conditions described elsewhere [5,6]. Different metal-NCFs have been produced by laser irradiation of dichlorobis(triphenylphosphine)nickel(II)  $[\text{NiCl}_2(\text{PPh}_3)_2]$ , dichlorobis(triphenylphosphine)cobalt(II)  $[\text{CoCl}_2(\text{PPh}_3)_2]$ , and [1,2-bis(diphenylphosphino)ethane]dichloroiron(II)  $[\text{FeCl}_2(\text{Dppe})]$ . P-free metal-NCFs were produced using bis(benzonitrile)

dichloropalladium(II)  $[\text{PdCl}_2(\text{PhCN})_2]$ , dichloro(1,10-phenanthroline)palladium(II)  $[\text{PdCl}_2(\text{Phen})]$ , and (2,2'-bipyridine)dichloropalladium(II)  $[\text{PdCl}_2(\text{Bipy})]$ . Naphthalene, phenanthrene, and 1,10-phenanthroline have been used as precursors for the synthesis of metal-free, P-free NCFs. All chemicals were purchased from Sigma-Aldrich (Schnelldorf, Germany and Saint-Quentin-Fallavier, France) and used as received.


The structure of the synthesized NCFs was imaged by scanning electron microscopy (SEM, Hitachi S-3400N (Hitachi, Ltd., Chiyoda-ku, Japan), including a Röntec XFlash detector (Röntec GmbH, Berlin, Germany) for energy dispersive X-ray spectroscopy (EDS) analyses), and transmission electron microscopy (TEM, JEOL JEM-3000F microscope, JEOL Ltd., Akishima-shi, Japan, equipped with an Oxford Instruments ISIS 300 X-ray microanalysis system and a Link Pentafet detector, Oxford Instruments, Abingdon, UK, for EDS analyses). NCF thermal stability in air was studied by thermogravimetric analysis (TGA, SETARAM Setsys Evolution, Hillsborough, NJ, USA; samples were analyzed in Pt pans at a heating rate of  $10^\circ\text{C}/\text{min}$  up to  $850^\circ\text{C}$  in an atmosphere of air flowing at  $100\text{ mL}/\text{min}$ ). Micro-Raman spectroscopy studies were carried out using a Dilor XY Raman spectrometer ( $\lambda_{\text{exc}} = 514.5\text{ nm}$ , HORIBA, Ltd., Kyoto, Japan). Elemental analyses of metal-free NCFs were performed using a Thermo Flash EA 1112 Series NC analyzer (Thermo Fisher Scientific, Waltham, MA, USA). The textural properties of NCFs were studied using nitrogen adsorption-desorption isotherms measured at  $77\text{ K}$  (Micromeritics ASAP 2020, Norcross, GA, USA) and using the Brunauer-Emmett-Teller (BET) method between 0.05 and 0.3  $P/P_0$  and t-Plot and Barret-Joyner-Halenda (BJH) method. Density values were measured using an AccuPyc II 1340 Micromeritics helium picnometer (Micromeritics, Norcross, GA, USA).

Fiber spinning of NCF biocomposites was performed by injecting 1:4 Au-NCF:sodium alginate (MW: 400K) aqueous dispersions ( $1\text{ mg}/\text{mL}$  Au-NCF prepared by bath sonication) into a coagulation bath (5%  $\text{CaCl}_2$  solution in 70%





**Figure 3** TEM characterization of the different components of NCFs. TEM images of NCFs produced using  $[\text{PdCl}_2(\text{PhCN})_2]$  (a),  $[\text{NiCl}_2(\text{PPh}_3)_2]$  (b),  $[\text{CoCl}_2(\text{PPh}_3)_2]$  (c), and naphthalene (d) targets. Inset on (a) shows graphitic structures observed on  $[\text{PdCl}_2(\text{Phen})]$  foams (scalebar 50 nm).




**Figure 4** Raman spectra show typical features of high degree carbon disorder in NCFs produced from naphthalene. The high degree of carbon disorder in NCFs produced by laser ablation of naphthalene is also demonstrated by the presence of broad bands centered at approximately  $1360\text{ cm}^{-1}$  (D-band) and approximately  $1590\text{ cm}^{-1}$  (G-band) of equivalent intensities in Raman spectra.

**Table 1** Measured densities of different carbon materials

Carbon material	Density ( $\text{g/cm}^3$ )
NCF	1.66
Multi-walled carbon nanotubes <sup>a</sup>	1.98
Nanodiamond <sup>b</sup>	2.97
Graphitic cones <sup>c</sup>	1.96
Carbon aerogel	0.20 to 1.00 [10,11]
Carbon xerogel <sup>d</sup>	1.73
Carbon black <sup>e</sup>	1.91
Activated carbon <sup>f</sup>	2.05
Graphite <sup>g</sup>	2.27
Ordered mesoporous carbon <sup>h</sup>	1.63
Carbon nanofoam	0.020 to 0.002 [12]

<sup>a</sup>High-purity multi-walled carbon nanotubes produced by the CVD technique (10 to 15 nm in diameter,  $\geq 10$  microns in length; Nanothinx S.A.);

<sup>b</sup>Nanodiamonds, purified, grade G01 (PlasmaChem); <sup>c</sup>Graphitic cones produced by hydrocarbon pyrolysis (n-TEC) [13]; <sup>d</sup>Carbon xerogels prepared by polycondensation of resorcinol and formaldehyde in water by Pekala's sol-gel method [14]; <sup>e</sup>Vulcan XC-72R carbon black (Delta Tecnic S.A.); <sup>f</sup>Activated carbon (Morgui Clima S.L.); <sup>g</sup>Graphite, particle size  $< 50\ \mu\text{m}$  (Merck); <sup>h</sup>Ordered mesoporous carbon synthesized using a template-mediated process [15].



**Figure 5** NCFs easily disperse in various solvents. Top image shows NCFs in different solvents 60 s after being dispersed by mild sonication. Bottom image shows the same dispersions after 48 h. Solvents: 1-water, 2-acetone, 3-ethanol, 4-diethyl ether, 5-toluene, 6-dichlorometane, 7-hexane.

methanol) following the carbon nanotube biofiber spinning procedure reported by Razal et al. [7]. The electrical conductivity of the spun fibers was characterized by four-probe resistance measurements using a Keithley 2000 Multimeter (Keithley Instruments, Inc., Cleveland, OH, USA).


## Results and discussion

SEM (Figure 2), TEM (Figure 3), and EDX characterization of the soot that resulted from the laser irradiation of different organometallic targets show that our laser ablation technique is not only restricted to the synthesis of Au/NCFs and Cu/NCFs [5,6], but it can also provide a new family of metal-NCF hybrids of any desired metal. These metal-NCFs exhibit a spongy-like microstructure (Figure 2a) as a result of nanoparticle assembly. These nanoparticles consist of amorphous carbon particles, graphitic nanostructures, and metal nanoparticle-containing amorphous carbon aggregates (Figure 3a,b,c). Moreover, metal-NCFs that result from the laser irradiation of  $[\text{PdCl}_2(\text{PhCN})_2]$ ,  $[\text{PdCl}_2(\text{Phen})]$ ,

and  $[\text{PdCl}_2(\text{Bipy})]$  also indicate that aromatic ligands different than  $\text{PPh}_3$  and without phosphor in their composition, such as benzonitrile, 1,10-phenanthroline, or 2,2'-bipyridine, can also efficiently act as carbon source for the laser production of carbon matrices (Figures 2 and 3).

Based on these findings, we then irradiated different aromatic compounds toward the synthesis of metal-free and P-free NCFs. Thus, laser ablation of naphthalene, phenanthrene, and 1,10-phenanthroline resulted in the formation of a NCF material which consisted of both amorphous carbon aggregates and graphitic nanodomains (Figures 2b and 3d). Elemental analysis data reveal high carbon contents ( $\geq 95\%$ ) for these metal-free NCFs. The extensive charging observed in NCFs without any conductive coating deposited on conducting carbon films for SEM characterization reveals the nonconducting nature of these materials. The Raman spectra of the metal-free NCFs show broad D- and G-bands of comparable intensities, a feature typical of short-range  $sp^2$ -bonded carbons [6,8]. As an example, we show in Figure 4 the spectrum of NCFs produced by laser ablation of naphthalene. The much broader aspect of the D-band (as compared to the G-band) indicates that this material lacks long-range graphitic order. According to Ferrari's model of graphite amorphization path [8], this material would be in stage 2 of amorphization (denoted as  $sp^2$  a-C in [8]) in which only some  $sp^2$ -bonded rings remain, thus confirming the predominance of amorphous carbon already observed by TEM.

TGA analyses show that metal-free NCFs are thermally stable in air up to temperatures of approximately  $600^\circ\text{C}$ . It is interesting to point out that the temperature of maximum decomposition rate of NCFs produced by laser ablation of  $\text{PPh}_3$  (which contains 8.2% P) is about  $30^\circ\text{C}$  higher than that of the naphthalene-produced NCFs, probably as a result of flame retardant role of P [9]. The study of the textural properties reveals that NCFs produced by laser ablation of  $\text{PPh}_3$  and naphthalene are mesoporous materials with BET surface areas between 33 and  $63\text{ m}^2/\text{g}$  and mesopore volumes of 0.046 to  $0.168\text{ cm}^3/\text{g}$ , respectively. The measured BET surface



**Figure 6** SEM micrographs of Au-NCF/alginate composite biofibers. SEM micrographs show a fiber overview (a) and the microstructure at the fiber cross-section (b).

area values are lower than those of other carbon materials consisting of amorphous carbon aggregates such as carbon aerogels (typical values in the range 400 to 600 m<sup>2</sup>/g) [10,11] and carbon nanofoams (300 to 400 m<sup>2</sup>/g) produced by femtosecond pulsed laser ablation of HOPG [12]. Additionally, density values of 1.66 g/cm<sup>3</sup> have been measured for naphthalene-produced NCFs by He picnometry. These values are similar to those of other carbon materials (Table 1) such as multi-walled carbon nanotubes, carbon xerogels, carbon black, graphitic cones, and ordered mesoporous carbon but significantly higher than those reported for carbon nanofoams produced by ultrafast lasers (0.02 to 0.002 g/cm<sup>3</sup>) [12].

NCFs are collected from laser ablation processes as intractable soots. In order to evaluate the potential chemical processing capabilities of our NCFs, these materials were dispersed in different solvents. Mild (bath) sonication resulted in NCF dispersions which are stable for over 48 h in all tested solvents but in hexane (Figure 5). This NCF remarkable dispersibility opens new opportunities toward the incorporation of these nanocarbons into functional materials and assemblies. Thus, Au-NCF/alginate biocomposite fibers, tens of centimeters in length and 30 to 50 micrometers in diameter (Figure 6), were spun by coagulation of sodium alginate assisted Au-NCF aqueous dispersions in a CaCl<sub>2</sub> water/methanol solution, followed by RT drying in air of the resulting elastomeric gels. Four-probe resistance measurements revealed that these fibers were nonconducting. This fiber spinning method is an interesting strategy for easy NCF handling and for providing a confinement in the form of quasi 1D architectures to metal nanoparticles.

## Conclusions

The laser chemistry approach described in the present work is a versatile method for the synthesis of metal nanoparticles embedded in carbon matrices from molecular precursors. This laser chemistry is very appealing for applications requiring metal nanoparticles largely isolated from each other embedded in solid matrices. Moreover, it can be used for the synthesis of metal-free, P-free NCFs from commercial organic precursors, which would in turn facilitate upscaling their production. On the other hand, the chemical processing capabilities of NCFs ease their handling and may open attractive opportunities toward their incorporation into matrices and applications. Future challenges should deal with the design of production or processing strategies to increase the surface area and conductivity of these materials to enable their use as, for example, electrode materials, in catalysis, or as functional magnetic materials.

## Competing interests

The authors declare that they have no competing interests.

## Authors' contributions

ASA, RL, GFF, and EM carried out the laser ablation experiments. EM, GFF, ML, and ASA conceived the study. MLS performed the Raman characterization. ASA carried out the electron microscopy and physicochemical characterization, and completed the data analysis. RG was in charge of further physicochemical studies and assisted in data analysis. JMR and EM performed the fiber spinning experiments. RG and EM drafted the manuscript. All authors read and approved the final manuscript.

## Acknowledgments

This work has been supported by the regional Government of Aragón (Spain, Project PI119/09, and E101 and T87 Research Groups funding) and the Spanish Government and Feder funds through grant MAT2010-19837-C06-06. This work has been funded in part by the European Commission through projects LIFE11/ENV/ES 560 and grant agreement no. 280658. The authors would like to acknowledge the use of Servicio de Microscopia Electrónica (Servicios de Apoyo a la Investigación), Universidad de Zaragoza. The authors also thank the technical assistance provided by the Servicio de Análisis de the Instituto de Carboquímica ICB-CSIC. The authors thank María Jesús Lázaro for kindly providing carbon xerogel and ordered mesoporous carbon samples. Carbon black and activated carbon samples were kindly supplied by Delta Tecnic S.A. and Morgui Clima S.L, respectively.

## Author details

<sup>1</sup>Instituto de Carboquímica ICB-CSIC, Miguel Luesma Castán 4, 50018 Zaragoza, Spain. <sup>2</sup>Departamento de Química Física, Universidad de Zaragoza, C/Pedro Cerbuna s/n, 50009 Zaragoza, Spain. <sup>3</sup>Instituto de Ciencia de Materiales de Aragón, Universidad de Zaragoza-CSIC, 50009 Zaragoza, Spain. <sup>4</sup>ARC Centre of Excellence for Electromaterials Science and Intelligent Polymer Research Institute, AIIIM Facility, Innovation Campus, University of Wollongong, Wollongong, NSW 2522 Australia. <sup>5</sup>Instituto de Síntesis Química Catalísis Homogénea, Universidad de Zaragoza-CSIC, Plaza San Francisco s/n, 50009 Zaragoza, Spain.

Received: 17 November 2012 Accepted: 28 March 2013

Published: 16 May 2013

## References

- Muñoz E, Maser WK, Benito AM, Martínez MT, de la Fuente GF, Righi A, Sauvajol JL, Anglaret E, Maniette Y: **Single-walled carbon nanotubes produced by cw CO<sub>2</sub>-laser ablation: study of parameters important for their formation.** *Appl Phys A* 2000, **70**:145–151.
- Puretzky AA, Styers-Barnett DJ, Rouleau CM, Hu H, Zhao B, Ivanov IN, Geohagan DB: **Cumulative and continuous laser vaporization synthesis of single wall carbon nanotubes and nanohorns.** *Appl Phys A* 2008, **93**:849–855.
- Rode AV, Hyde ST, Gamaly EG, Elliman RG, McKenzie DR, Bulcock S: **Structural analysis of a carbon foam formed by high pulse-rate laser ablation.** *Appl Phys A* 1999, **69**:S755–S758.
- Choi M, Altman IS, Kim YJ, Pikhitsa PV, Lee S, Park GS, Jeong T, Yoo JB: **Formation of shell-shaped carbon nanoparticles above a critical laser power in irradiated acetylene.** *Adv Mater* 2004, **16**:1721–1725.
- Muñoz E, de Val M, Ruiz-González ML, López-Gascón C, Sanjuán ML, Martínez MT, González-Calbet JM, de la Fuente GF, Laguna M: **Gold/carbon nanocomposite foam.** *Chem Phys Lett* 2006, **420**:86–89.
- Muñoz E, Ruiz-González ML, Seral-Ascaso A, Sanjuán ML, González-Calbet JM, Laguna M, de la Fuente GF: **Tailored production of nanostructured metal/carbon foam by laser ablation of selected organometallic precursors.** *Carbon* 2010, **48**:1807–1814.
- Razal JM, Gilmore KJ, Wallace GG: **Carbon nanotube biofiber formation in a polymer-free coagulation bath.** *Adv Funct Mater* 2008, **18**:61–66.
- Ferrari AC, Robertson J: **Interpretation of Raman spectra of disordered and amorphous carbon.** *Phys Rev B* 2000, **61**:14095–14107.
- Gaan S, Sun G: **Effect of phosphorus and nitrogen on flame retardant cellulose: a study of phosphorus compounds.** *J Anal Appl Pyrolysis* 2007, **78**:371–377.
- Wu D, Fu R, Zhang S, Dresselhaus MS, Dresselhaus G: **Preparation of low-density carbon aerogels by ambient pressure drying.** *Carbon* 2004, **42**:2033–2039.
- Liu N, Zhang S, Fu R, Dresselhaus MS, Dresselhaus G: **Carbon aerogel spheres prepared via alcohol supercritical drying.** *Carbon* 2006, **44**:2430–2436.

12. Rode AV, Gamaly EG, Luther-Davies B: **Formation of cluster-assembled carbon nano-foam by high-repetition-rate laser ablation.** *Appl Phys A* 2000, **70**:135–144.
13. Krisnan A, Dujardin E, Treacy MMJ, Huggdahl J, Lynum S, Ebbesen TW: **Graphitic cones and the nucleation of curved carbon surfaces.** *Nature* 1997, **388**:451–454.
14. Alegre C, Calvillo L, Moliner R, González-Expósito JA, Guillén-Villafuerte O, Martínez Huerta MN, Pastor E, Lázaro MJ: **Pt and PtRu electrocatalysts supported on carbon xerogels for direct methanol fuel cells.** *J Power Sources* 2011, **96**:4226–4235.
15. Calvillo L, Lázaro MJ, García-Bordejé E, Moliner R, Cabot PL, Esparbé I, Pastor E, Quintana JJ: **Platinum supported on functionalized ordered mesoporous carbon as electrocatalyst for direct methanol fuel cells.** *J Power Sources* 2007, **169**:59–64.

doi:10.1186/1556-276X-8-233

**Cite this article as:** Seral-Ascaso et al.: 'Laser chemistry' synthesis, physicochemical properties, and chemical processing of nanostructured carbon foams. *Nanoscale Research Letters* 2013 **8**:233.

**Submit your manuscript to a SpringerOpen<sup>®</sup> journal and benefit from:**

- ▶ Convenient online submission
- ▶ Rigorous peer review
- ▶ Immediate publication on acceptance
- ▶ Open access: articles freely available online
- ▶ High visibility within the field
- ▶ Retaining the copyright to your article

---

Submit your next manuscript at ▶ [springeropen.com](http://springeropen.com)

---