University of Wollongong

Research Online

Australian Institute for Innovative Materials -
Papers

Australian Institute for Innovative Materials

1-1-2017

Same titanium glycolate precursor but different products: Successful synthesis of twinned anatase TiO₂ nanocrystals with excellent solar photocatalytic hydrogen evolution capability

Gang Cheng

Wuhan Institute of Technology

Yi Wei

Wuhan Institute of Technology

Jinyan Xiong

Wuhan Textile University, University of Wollongong, jx513@uowmail.edu.au

Yixin Gan

Wuhan Institute of Technology

Jiaxin Zhu

Wuhan Institute of Technology

See next page for additional authors

Follow this and additional works at: <https://ro.uow.edu.au/aiimpapers>

Part of the [Engineering Commons](#), and the [Physical Sciences and Mathematics Commons](#)

Research Online is the open access institutional repository for the University of Wollongong. For further information contact the UOW Library: research-pubs@uow.edu.au

Same titanium glycolate precursor but different products: Successful synthesis of twinned anatase TiO₂ nanocrystals with excellent solar photocatalytic hydrogen evolution capability

Abstract

Exploiting a synthesis protocol to tailor TiO₂ with a unique morphology and crystal phase has received considerable interest in the energy and environmental fields. We here describe the use of a titanium glycolate precursor in a hydrothermal hydrolysis reaction to engineer TiO₂ nanocrystals with different crystal phases and structures. Anatase TiO₂ nanocrystals with twinned structures were obtained by using a lower amount of NaOH in the hydrolysis system, while brookite TiO₂ nanocrystals were formed when higher amounts of NaOH were employed. The as-synthesized different TiO₂ nanocrystals have a suitable bandgap to harvest photons and a more negative bottom level of the conduction band than the redox potential of H⁺/H₂ indicating their potential as hydrogen-evolution semiconductor photocatalysts. However, the TiO₂ nanotwins show promoted charge separation efficiency, and thus result in superior photocatalytic H₂ generation activity compared to the anatase and brookite TiO₂ nanocrystals. Our findings provide an effective and versatile solution for the fabrication of TiO₂-based nanostructures with different phases and morphologies through chemical conversion of powder precursor nanoparticles, which could pave the way to the design of other functional nano-oxides with unique structures.

Disciplines

Engineering | Physical Sciences and Mathematics

Publication Details

Cheng, G., Wei, Y., Xiong, J., Gan, Y., Zhu, J. & Xu, F. (2017). Same titanium glycolate precursor but different products: Successful synthesis of twinned anatase TiO₂ nanocrystals with excellent solar photocatalytic hydrogen evolution capability. *Inorganic Chemistry Frontiers*, 4 (8), 1319-1329.

Authors

Gang Cheng, Yi Wei, Jinyan Xiong, Yixin Gan, Jiaxin Zhu, and Feifan Xu

RESEARCH ARTICLE

View Article Online

View Journal | View Issue

Cite this: *Inorg. Chem. Front.*, 2017, **4**, 1319

Same titanium glycolate precursor but different products: successful synthesis of twinned anatase TiO₂ nanocrystals with excellent solar photocatalytic hydrogen evolution capability†

Gang Cheng, *^a Yi Wei,^a Jinyan Xiong,^{b,c,d} Yixin Gan,^a Jiabin Zhu^a and Feifan Xu^a

Exploiting a synthesis protocol to tailor TiO₂ with a unique morphology and crystal phase has received considerable interest in the energy and environmental fields. We here describe the use of a titanium glycolate precursor in a hydrothermal hydrolysis reaction to engineer TiO₂ nanocrystals with different crystal phases and structures. Anatase TiO₂ nanocrystals with twinned structures were obtained by using a lower amount of NaOH in the hydrolysis system, while brookite TiO₂ nanocrystals were formed when higher amounts of NaOH were employed. The as-synthesized different TiO₂ nanocrystals have a suitable bandgap to harvest photons and a more negative bottom level of the conduction band than the redox potential of H⁺/H₂ indicating their potential as hydrogen-evolution semiconductor photocatalysts. However, the TiO₂ nanotwins show promoted charge separation efficiency, and thus result in superior photocatalytic H₂ generation activity compared to the anatase and brookite TiO₂ nanocrystals. Our findings provide an effective and versatile solution for the fabrication of TiO₂-based nanostructures with different phases and morphologies through chemical conversion of powder precursor nanoparticles, which could pave the way to the design of other functional nano-oxides with unique structures.

Received 21st May 2017,
Accepted 19th June 2017

DOI: 10.1039/c7qi00278e

rsc.li/frontiers-inorganic

1. Introduction

Titanium dioxide (TiO₂) is regarded as one of the most promising semiconducting materials on account of its excellent physicochemical properties and great potential in the energy and environmental fields. Evidence indicates that the performance of TiO₂-based materials can be varied by changing not only the crystal phase but also the structure of the TiO₂.^{1–3} Study of the intrinsic relationship between the phase/morphology and properties of TiO₂-based materials has engendered an urgent need for adjustable synthetic strategies, where the crystal phase and particle structure of TiO₂ nanomaterials can be precisely controlled with designed functionalities.^{4–9} However, synthetic techniques for preparing such nanostructured materials, especially those achieving simultaneous

control of both the crystal phase and the morphology, still remain a challenge because of the rapid hydrolysis of titanium alkoxides and titanium tetrachloride, which are widely used as titanium precursors. Therefore, on the one hand, much attention has been paid to the control of hydrolysis using alcohol or chelating agents, such as dihydric alcohol or carboxylic acid, or other additives.^{10–13} On the other hand, substantial efforts have been made toward the development of a new suitable titanium precursor with a proper transformation process to selectively prepare TiO₂ with tunable phases and structures, as well as avoiding the involvement of complex experimental processes.

One dimensional titanate nanofibers/nanorods/nanotubes are one of the most widely used precursors to prepare TiO₂ nanostructures *via* thermal dehydration reactions or hydrothermal treatments.^{14–19} However, the use of titanate nanowires derived from the alkali treatment of TiO₂ nanoparticles under highly basic conditions requires complex post-processing processes; meanwhile, TiO₂ nanocrystals prepared by the hydrothermal transformation of titanate are limited to a single crystal phase of anatase or rutile. Wang *et al.*²⁰ reported a one-pot and template-free strategy for synthesizing hollow TiO₂ nanostructures using titanocene dichloride (Cp₂TiCl₂) as the titanium source, but other chemicals (acetone and ammonia) were also involved in the reaction system. Other titanium

^aSchool of Chemistry and Environmental Engineering, Wuhan Institute of Technology, Xiongchu Avenue, Wuhan, 430073, PR China. E-mail: gchenglab@163.com

^bCollege of Chemistry and Chemical Engineering, Wuhan Textile University, Wuhan 430200, PR China

^cHubei Key Laboratory of Biomass Fibers and Eco-dyeing & Finishing, Wuhan Textile University, Wuhan, 430073 Hubei, PR China

^dInstitute for Superconducting and Electronic Materials, University of Wollongong, Innovation Campus, Squires Way, North Wollongong, NSW 2500, Australia

†Both Dr Cheng and Dr Xiong would like to send their congratulations on the occasion of the tenth anniversary of the foundation of Prof. Rong Chen's group.

precursors have also been prepared to fabricate TiO₂ nanomaterials. For example, TiO₂ nanoparticles were prepared with strict control of the size, molecular mass, and mass density by hydrolyzing a precursor, Ti(acac)₂(biphen), in the presence of a well-defined hollow Pd₁₂L₂₄ spherical endotemplate.²¹ Unique spindle-shaped nanoporous anatase TiO₂ mesocrystals with a single-crystal-like structure and tunable sizes were also successfully fabricated through calcination treatment of precursors prepared in a tetrabutyl titanate–acetic acid system under solvothermal conditions.²² In addition, titanium glycolate precursors prepared from titanium alkoxides and ethylene glycol are considered as a potential precursor for preparing TiO₂. Xia's group synthesized TiO₂ nanowires and nanospheres *via* annealing treatment of prepared titanium glycolate precursors, and demonstrated that the titanium glycolate could be transformed into the amorphous phase of TiO₂ at 350 °C, the anatase phase at 500 °C, and the rutile phase at 850 °C.^{23,24} Zhong *et al.* synthesized highly nanoporous TiO₂ (anatase) spheres *via in situ* hydrolysis of titanium glycolate precursor spheres.²⁵ However, the disadvantage of the above mentioned synthesis strategies is that the synthesized TiO₂ shows a similar morphology or size to the precursors, because the precursors act as a hard template in the process of annealing the precursor powders.

In previous work, we successfully synthesized TiO₂@carbon material hybrid nanostructures *via* a nanoprecursor-involved hydrothermal process,^{26–28} in which the spherical titanium glycolate precursors were hydrolyzed into titanium oxide from a nanoporous to a nanoparticulate structure. This phenomenon inspired us to manipulate the stability and transformation of titanium glycolate precursors by adjusting the experimental conditions involved in the wet-chemical synthesis and to study their effects on the formation and growth of the final TiO₂ nanocrystals. Herein, the structure and crystal phase of the TiO₂ products were successfully engineered from this titanium glycolate precursor *via* the use of NaOH, which was confirmed by powder X-ray diffraction and scanning/transmission electron microscopy. To the best of our knowledge, there are few literature reports related to the phase and structure controlled synthesis of TiO₂ through a wet-chemical approach using powder precursors. Interestingly, twinned anatase TiO₂ nanocrystals were prepared for the first time in the presence of a lower amount of NaOH, and also displayed promoted charge separation efficiency for a superior photocatalytic capability towards hydrogen generation.

2. Experimental section

2.1 Synthesis

All of the reagents were of analytical grade and were used without further purification. De-ionized water was used in all experiments. The titanium glycolate precursor was synthesized according to our previously reported procedure.^{26,29,30} In a typical synthesis, 2 mL of tetrabutoxytitanium was added to 50 mL of ethylene glycol and was magnetically stirred for

2 hours at 60 °C in a water bath. After cooling down to room temperature, the mixture was poured into a mixed solution of acetone and de-ionized water (v/v = 150 mL/30 mL). The precipitate was collected and washed with de-ionized water and ethanol six times by centrifugation, then dried at 60 °C overnight for further use.

Twinned TiO₂ nanocrystals were prepared by a hydrothermal method from the as-synthesized titanium glycolate precursor. In a typical synthesis, 0.1 g of the as-synthesized titanium glycolate precursor was dispersed in 30 mL of de-ionized (DI) water under vigorous sonication. Next, 0.5 mmol NaOH was added into the above homogeneous solution and then the mixture was transferred into a 50 mL Teflon-lined autoclave and maintained at a temperature of 180 °C for 18 h. After cooling down to room temperature, the products were collected and washed with de-ionized water and ethanol several times by centrifugation. The final product was dried for 12 h at 60 °C. The effect of the amount of NaOH on the formation and structure of the twinned TiO₂ nanocrystals was investigated under the same synthesis conditions, except for the tuning of the NaOH concentration.

2.2 Characterization

The titanium glycolate precursor and TiO₂ samples were characterized by powder X-ray diffraction (XRD), scanning electron microscopy (SEM), transmission electron microscopy (TEM), and selected area electron diffraction (SAED). XRD was carried out on a multi-purpose high performance X-ray diffractometer (CuKα radiation, λ = 1.54 Å) at a scanning rate of 0.03° s^{−1} in the 2θ range from 10° to 90°. SEM images were taken on a field-emission electron microscope (ZEISS, SUPRA 40VP) operating at an acceleration voltage of 3 kV. TEM images, high resolution TEM images, and SAED patterns were recorded on a JEOL 2010 electron microscope at an accelerating voltage of 200 kV. Photoluminescence spectra (PL) were detected with a HITACHI (Japan) F4600 Fluorescence spectrophotometer.

The photocurrent measurements were performed similar to previous reports²⁸ and conducted on a CHI 660E electrochemical system (Shanghai, China) using a standard three-electrode cell with a working electrode, a platinum wire counter electrode, and a saturated calomel electrode (SCE) reference electrode. A solution containing 0.5 M Na₂SO₄ was used as the electrolyte. The working electrode was prepared according to the following process: 20 mg of as-prepared sample was mixed with 1 mL of DMF and 0.01 mL of Nafion solution (5%, DuPont) to form a homogeneous ink. Then 0.1 mL of the photocatalyst ink was dip-coated onto a 10 mm × 10 mm indium–tin oxide (ITO) glass electrode. The estimated loading amount of the sample is 2 mg cm^{−2}. After drying at room temperature, the as-prepared electrode was further annealed at 150 °C for 4 h in a vacuum oven to remove the resin. The photocurrent responses of the photocatalyst in the presence and absence of light were measured at open-circuit potential, with simulated light irradiation provided by a 500 W Xe lamp. Electrochemical impedance spectroscopy (EIS) was

carried out at open-circuit potential in 0.5 M potassium ferricyanide solution. The samples were dip coated onto a glassy carbon working electrode. A sinusoidal AC perturbation of 5 mV was applied to the electrode over the frequency range of 0.5–10⁵ Hz.

2.3 Photocatalytic hydrogen generation test

Photocatalytic hydrogen evolution experiments were conducted under vacuum conditions in a 500 mL quartz reactor with a top quartz window allowing for light irradiation (CEL-SPH2N, CEAULIGHT Beijing). Actually, the procedure is similar to our previous method.³¹ Typically, 50 mg of photocatalyst was added into methanol solution (vol 20%), which was used as a sacrificial electron donor, and the mixture was subjected to ultrasonic treatment for 15 min. A 300 W Xe lamp was used as an artificial sunlight source. Before light irradiation, the quartz reactor was sealed gas-tightly with high vacuum grease and purged by vacuumization to remove the residual air. During the hydrogen generation reaction, the suspension was exposed under simulated solar light irradiation with continuous stirring. The volume of generated hydrogen was analyzed by on-line gas chromatography with a TCD detector at set intervals. All the hydrogen evolution experiments were carried out at room temperature.

3. Results and discussion

Fig. 1a shows the XRD pattern of the sample prepared from the titanium glycolate nanoprecursor with the involvement of 0.5 mmol NaOH in the reaction system. All diffraction peaks can be assigned to the anatase phase (JCPDS no. 71-1167), which confirmed the high purity of the product. The microstructural characteristics of the TiO₂ material were also analysed by Raman scattering. As shown in Fig. 1b, the material displays four bands at 152, 400, 516, and 637 cm⁻¹, corresponding to the characteristic Raman modes E_g(1), B_{1g}(1), A_{1g} + B_{1g}(2), and E_g(2) of anatase TiO₂, respectively. This indicates the presence of the anatase phase in the as-prepared materials, which is in accordance with the XRD results.

The morphology and structure of the as-synthesized TiO₂ sample were further characterized using SEM, TEM, and HRTEM images, and SAED patterns. In Fig. 2a, it was observed from the SEM image that large amounts of nanoparticles were obtained. The TEM image shown in Fig. 2b reveals that the TiO₂ nanoparticles have a diameter of about 50 nm. Furthermore, it could be seen that some nanoparticles have a shared edge like a fastigium. The HRTEM images (Fig. 2d and e) clearly depict that the TiO₂ nanoparticles have a twinned structure and two nanocrystals share a back like a fastigium in a Beijing traditional courtyard (Fig. 2c), which might be attributed to the growth occurring along the same zone axis. As shown in Fig. 2d, the distance between the two consecutive planes from the central of such twinned nanocrystals is measured to be 0.35 nm from the lattice image, which matches the distance between two consecutive (101) planes of

Fig. 1 (a) XRD pattern and (b) Raman spectrum of the as-synthesized twinned TiO₂ anatase nanocrystals.

bulk TiO₂, indicating that the twinned nanocrystals have the same exposed facets.³² The SAED pattern in Fig. 2f was characteristic of a polycrystalline structure of TiO₂, and several diffraction ring patterns corresponding to the (101), (004), (200), and (211) planes are the sum of different single-crystallized TiO₂ nanoparticles.

As a matter of fact, it was found that the amount of NaOH has a significant impact on the structure and crystal phase of the final titanium oxide nanocrystals. Fig. 3 shows the XRD patterns of the as-synthesized products in the presence of different amounts of NaOH. It was found that a low concentration of NaOH could not tailor the crystal phase, and the final products exhibit the anatase phase when less than 0.5 mmol NaOH is used. As shown in Fig. 4a and b, the as-prepared titanium glycolate precursor exhibits an amorphous phase and aggregated nanoparticulate morphology. When the precursor powders were hydrothermally treated in water, the XRD pattern in Fig. 3 and the TEM image in Fig. 4c show that anatase TiO₂ nanocrystals with cube-like morphology were fabricated. Fig. 4d displays the corresponding HRTEM image of a single cube-like TiO₂ nanoparticle. It shows a *d*-spacing of about 0.35 nm, which is in good agreement with the (101) lattice plane of anatase TiO₂, suggesting that the cube-like nanocrystals were well-crystallized. When a small amount of NaOH was added to the above reaction system, anatase TiO₂

Fig. 2 (a) SEM, (b) TEM, and (d and e) HRTEM images, and (f) SAED pattern of the as-synthesized twinned TiO_2 anatase nanocrystals. (c) Photograph of a Beijing traditional courtyard.

Fig. 3 XRD patterns of the titanium glycolate precursor and TiO_2 products synthesized under different conditions.

nanocrystals were still formed as shown in the TEM image in Fig. 4e. Interestingly, the HRTEM image in Fig. 4f indicates that the as-formed nanocrystals have a twinned structure like a fastigium. The above results reveal that the involvement of NaOH is the key parameter for the formation of the twinned TiO_2 nanocrystals.

However, with an increase in the amount of NaOH, the crystal phase and structure of the fabricated TiO_2 nanocrystals changed greatly. As shown in Fig. 5, when the concentration of NaOH increased from 0.75 to 4 mmol in the reaction system, TiO_2 with a brookite phase was obtained, instead of anatase phase TiO_2 . As depicted in Fig. 6a–c, the SEM and TEM images show that rice-like brookite TiO_2 nanoparticles were fabricated in the presence of 0.75 mmol NaOH. Furthermore, in Fig. 6d–f, it was found that large amounts of particulates and fewer rice-like nanoparticles were obtained when 1 mmol NaOH was involved in the reaction system. When further increasing the concentration of NaOH, the distribution of different-shaped brookite TiO_2 nanoparticles

Fig. 4 (a and b) SEM and TEM images of the titanium glycolate precursor; (c and d) TEM images of the TiO_2 products synthesized without NaOH; (e and f) TEM images of the TiO_2 products synthesized with 0.25 mmol NaOH.

Fig. 5 XRD patterns of the TiO_2 products synthesized with different concentrations of NaOH.

changed. As displayed in Fig. 6g–i, in the presence of 4 mmol NaOH, the final products mainly consisted of rice-like nanoparticles.

The above results further confirm that incorporating NaOH into the reaction system could achieve the tailoring of the crystal phase and morphology of the titanium oxide nanocrystals from the titanium glycolate precursor. Scheme 1 illustrates the formation of titanium oxide nanocrystals with different crystal phases and structures through the use of different amounts of NaOH in the reaction system. It is well-known that TiO_2 has three main phases, anatase, brookite and rutile, but solution-phase synthesis strategies for TiO_2 generally favour the formation of anatase structures. One of the main reasons for this is that the surface energy of anatase is lower than that of rutile and brookite.^{33,34} However, the nucleation and growth of different polymorphs of TiO_2 is also determined by the involvement of the precursor, which depends on the reagents used in the reaction system. For example, Coronado *et al.* synthesized anatase nanoparticles using acetic acid from amorphous titania, while they obtained phase-pure rutile and brookite nanoparticles with hydrochloric acid at a different concentration.³⁵ Zhao *et al.* also found that the initially formed precursor of $[\text{Ti}(\text{OH})_4(\text{OH}_2)_2]$ from the starting material TiOSO_4 in water could be easily transformed into the anatase phase, but the production of the brookite phase rather than other crystalline titania phases was favoured in the presence of highly con-

Fig. 6 SEM and TEM images of the TiO_2 products synthesized with the use of different amounts of NaOH: (a–c) 0.75 mmol, (d–f) 1 mmol, and (g–i) 4 mmol.

Scheme 1 Illustration of the phase and structure tailoring of titanium oxide nanocrystals in the presence of different concentrations of NaOH.

centrated OH^- .³⁶ Based on the above previous reports, we proposed that the titanium glycolate precursor could initially steadily convert into the building unit monomers of TiO_2 in the hydrothermal reaction system. Once the concentration of monomers reaches super-saturation, fast nucleation would occur, and a lot of crystal seeds would start to come out during the reaction period. However, the involvement of OH^- could affect the kinetics and thermodynamics in the nucleation and growth of such crystal seeds, resulting in the control of the crystal phase and structure. As the results revealed, the tita-

nium glycolate precursor hydrothermally treated with a slightly lower concentration of OH^- species could result in the formation of twinned anatase nanocrystals. Meanwhile, with the incorporation of highly concentrated OH^- into the present system, the precursor could be transformed into the brookite phase with a rice-like structure through a dissolution–recrystallization and subsequent crystal phase transformation process. Our understanding of the formation mechanism is limited and further study of the influence of additives on the structure and phase transformation of titanium oxides is still in progress.

Diffuse reflectance spectroscopy was used to characterize the optical absorption properties of the as-obtained TiO_2 materials. To compare the optical and related photocatalytic properties, the samples prepared in the presence of 0, 0.5 and 4 mmol NaOH, corresponding to anatase, twinned anatase, and brookite TiO_2 nanocrystals, respectively, were investigated in the following experiments. As shown in Fig. 7a, the UV-Vis diffuse reflectance spectra of the as-synthesized TiO_2 nanocrystals demonstrate that the products have different absorption edges in the UV-visible light region. Fig. 7b shows the plot of $(\alpha h\nu)^{1/2}$ versus photon energy ($h\nu$) for the as-synthesized TiO_2 nanocrystals, where α , ν , and h are the absorption coefficient, the light frequency, and a constant, respectively. The band gap energy (E_g value) of the anatase TiO_2 nanocrystals estimated from the plot of $(\alpha h\nu)^{1/2}$ versus photon energy ($h\nu$) was about 3.06 eV. However, the band gap energy of both the twinned anatase and brookite TiO_2 nanocrystals is narrower than that of the anatase TiO_2 nanocrystals (shown in Table 1), which confirms that the crystal phase and structure of TiO_2 have a significant impact on the optical properties and offer a way of tuning the band gap. The valence band (E_{VB}) and conduction

Fig. 7 (a) UV-vis diffuse reflectance spectra and (b) plots of $(\alpha h\nu)^{1/2}$ versus photon energy ($h\nu$) of the as-synthesized TiO_2 samples.

Table 1 Physicochemical properties, band gap, band edges, BET surface areas and photocatalytic H_2 evolution capability of the as-synthesized TiO_2 nanocrystals

Sample	S_{BET} ($\text{m}^2 \text{g}^{-1}$)	Band gap (eV)	E_{CB} (eV)	E_{VB} (eV)	H_2 generation ($\mu\text{mol g}^{-1} \text{h}^{-1}$)
Anatase TiO_2	141.19	3.06	-0.22	2.84	104.54
Twinned anatase TiO_2	76.84	2.96	-0.17	2.79	1272.66
Brookite TiO_2	54.98	2.87	-0.13	2.74	182.76

band (E_{CB}) edge of the TiO_2 nanocrystals at the point of zero charge can be calculated according to the empirical equation $E_{\text{VB}} = X - E^e + 0.5E_{\text{g}}$, in which X is the electronegativity of TiO_2 (5.81 eV), E^e is the energy of free electrons on the hydrogen scale (about 4.5 eV), E_{g} is the band gap energy of the semiconductor, and E_{CB} can be determined using $E_{\text{CB}} = E_{\text{VB}} - E_{\text{g}}$. The E_{VB} and E_{CB} of the samples were calculated and are summarized in Table 1. Typically, all three kinds of TiO_2 nanocrystals have a suitable bandgap to harvest photons and a more negative bottom level of the conduction band than the redox potential of H^+/H_2 , which is a thermodynamic requirement for

hydrogen-evolution semiconductor photocatalysts.³⁷ In other words, when incident light possessing energy greater than the band gap hits these TiO_2 materials, the photo-generated electrons could reduce the protons or water molecules on the surface of TiO_2 into molecular hydrogen.

Photocatalytic hydrogen evolution over the different TiO_2 nanocrystals was evaluated using methanol solution (vol 20%) as a sacrificial reagent under artificial sunlight irradiation. It was found that no H_2 generation was measured without any photocatalyst or light irradiation. These results confirmed that achieving photocatalytic H_2 production requires the use of a TiO_2 photocatalyst as well as the involvement of light irradiation. Fig. 8a and b display the capability and corresponding evolution rates of photocatalytic H_2 evolution using the different TiO_2 photocatalysts. It was observed that the anatase TiO_2 nanocrystals exhibited photocatalytic H_2 performance with a hydrogen generation rate of $104.54 \mu\text{mol g}^{-1} \text{h}^{-1}$, while the brookite TiO_2 nanocrystal photocatalyst had a hydrogen generation rate of $182.76 \mu\text{mol g}^{-1} \text{h}^{-1}$. However, when the twinned anatase TiO_2 nanocrystals were used as the photocatalyst, they showed remarkably enhanced photocatalytic H_2 generation capability with an evolution rate of $1272.66 \mu\text{mol g}^{-1} \text{h}^{-1}$. The hydrogen evolution rate value of twinned anatase TiO_2 ($1272.66 \mu\text{mol g}^{-1} \text{h}^{-1}$) was significantly larger than that of commercial P25 ($3.64 \mu\text{mol g}^{-1} \text{h}^{-1}$).³¹ In addition, it exhibited higher efficiency for hydrogen generation compared to porous TiO_2 hollow spheres ($21.2 \mu\text{mol g}^{-1} \text{h}^{-1}$),³⁸ 3D flower-like TiO_2 nanosheets ($1000 \mu\text{mol g}^{-1} \text{h}^{-1}$),³⁹ and TiO_2 nanoparticles ($13.7 \mu\text{mol g}^{-1} \text{h}^{-1}$).⁴⁰ In particular, as shown in Fig. 8c and d, the hydrogen evolution rate of the twinned TiO_2 nanocrystals was still maintained at about $500.74 \mu\text{mol g}^{-1} \text{h}^{-1}$ after three cycles, which is higher than that of both the anatase and brookite TiO_2 nanocrystals, indicating that the twinned TiO_2 nanocrystals have good stability towards hydrogen evolution.

It has been reported that the BET surface area and charge transfer have an influence on the photocatalytic hydrogen evolution capability of semiconductors.⁴¹ Herein the impact of the surface areas of the three kinds of different TiO_2 nanocrystals was first studied using nitrogen adsorption and desorption measurements. As shown in Fig. 9, the nitrogen adsorption-desorption isotherms of the three different TiO_2 nanocrystals exhibit type II adsorption-desorption isotherms in the range of 0.5–1.0 P/P_0 , indicated that the samples have a porous structure, which may result from the aggregation of small nanoparticles. The Brunauer-Emmett-Teller (BET) specific surface areas of the TiO_2 nanocrystals were calculated and are listed in Table 1. It was found that the BET surface area of the anatase TiO_2 nanocrystals was larger than that of twinned anatase TiO_2 , which was slightly higher than that of the brookite nanoparticles. However, the twinned anatase TiO_2 nanocrystals exhibited the highest photocatalytic hydrogen generation capability, even though they did not have the largest surface area among the three samples. These results indicate that the surface area is not the main parameter influencing the H_2 production performance of the three TiO_2 samples.

Fig. 8 (a) Photocatalytic hydrogen evolution performance and (b) evolution rate of the different TiO_2 photocatalysts. (c) Recyclability of the hydrogen evolution behavior and (d) corresponding evolution rate over the twinned TiO_2 nanocrystals.

Fig. 9 N_2 adsorption-desorption isotherms of the different TiO_2 photocatalysts.

Fig. 10 Photoluminescence spectra of the different TiO_2 photocatalysts.

The photoluminescence spectrum (PL) could give useful information about the efficiency of electron-hole recombination and charge carrier trapping. Particularly, the recombination of photogenerated electrons and holes produced in a semiconductor could induce PL. Accordingly, a lower PL intensity of a semiconductor indicates faster separation and better transfer efficiency of photoinduced electron-hole pairs in the photocatalysis system, and therefore displays a higher photocatalytic capability.^{42–44} As can be seen in Fig. 10, the PL intensity of twinned anatase TiO_2 was much lower than that of both

anatase and brookite TiO_2 . This result suggested that the TiO_2 nanocrystals with twinned structure could facilitate charge transfer so as to prohibit charge recombination in the TiO_2 nanocrystals and finally result in a higher photocatalytic hydrogen evolution capability.

To better understand the behavior of photo-induced charge carriers in the three kinds of different TiO_2 photocatalysts, additional electrochemical and photoelectrochemical experiments were also carried out. Fig. 11a shows the rapid and consistent photocurrent responses for each switch-on and -off

Fig. 11 (a) Electrochemical impedance spectra and (b) photocurrent responses of the different TiO₂ samples.

event in multiple 30 s on-off cycles under simulated solar light irradiation. It is worth noting that the photocurrent density of the twinned anatase TiO₂ electrode is much higher than that of both the anatase and brookite TiO₂ nanocrystals. The promoted photocurrent response of the sample indicates higher efficiency and lower recombination rate of photogenerated electron-hole pairs in the twinned anatase TiO₂ nanocrystals.^{45,46} Fig. 11b shows the electrochemical impedance spectroscopy (EIS) Nyquist plots of the as-prepared three kinds of TiO₂ photocatalysts. The arc radius on the EIS Nyquist plot of the twinned anatase TiO₂ photocatalyst is smaller than that of the anatase and brookite TiO₂ nanoparticles. As a matter of fact, in the EIS Nyquist plot, the smaller semicircle size indicates fast interfacial charge transfer in the semiconductor.^{47,48} The above result suggests that more effective interfacial charge transfer occurs on the twinned anatase TiO₂ photocatalyst rather than anatase and brookite TiO₂ under these conditions. Based on these results, it was concluded that the enhancement of the photocatalytic hydrogen evolution activity of the twinned anatase TiO₂ nanocrystals was attributed to the faster separation of photogenerated carriers and lower recombination of photoinduced electron-hole pairs.

4. Conclusions

In summary, anatase TiO₂ nanocrystals with a unique twinned nanostructure were successfully synthesized by a facile hydrothermal method from the hydrolysis of a titanium glycolate powder precursor. The composition and phase purity of the TiO₂ products were characterized by XRD and Raman spectroscopy. The SEM, TEM, and HRTEM images showed that the involvement of NaOH was not only a key parameter for the formation of twinned anatase TiO₂ nanocrystals, but could also be used to tailor the crystal phase of the as-synthesized TiO₂ by changing its concentration. The photocatalysis activities of the as-prepared TiO₂ products were evaluated by photocatalytic hydrogen generation under solar light irradiation. The excellent photocatalytic activity of twinned anatase TiO₂ towards H₂ production is ascribed to the efficient generation and separation of photoinduced electron-hole pairs. This novel approach using precursor nanoparticles offers a simple way to prepare TiO₂ nanocrystals with unique twinned structures and excellent photocatalytic hydrogen production capability, as well as tailor the morphology and crystal phase, and is expected to provide a reference for fabricating other functional oxide nanocrystals with designed structures and promising applications.

Acknowledgements

This work was supported by the National Natural Science Foundation of China (21501137) and Department of Education of Hubei Province under the project of Science and Technology Innovation Team of Outstanding Young and Middle-aged Scientists (T201606). Dr Cheng would like to thank Mr Fan Tian (WIT) for his help with the BET surface area measurements. The authors are grateful for the assistance of Professor Rong Chen (WIT) with some of the measurements.

References

- 1 E. J. W. Crossland, N. Noel, V. Sivaram, T. Leijtens, J. A. Alexander-Webber and H. J. Snaith, Mesoporous TiO₂ single crystals delivering enhanced mobility and optoelectronic device performance, *Nature*, 2013, **495**(7440), 215–219.
- 2 S. Yang, B. X. Yang, L. Wu, Y. H. Li, P. Liu, H. Zhao, Y. Y. Yu, X. Q. Gong and H. G. Yang, Titania single crystals with a curved surface, *Nat. Commun.*, 2014, **5**, 5355.
- 3 H. G. Yang, C. H. Sun, S. Z. Qiao, J. Zou, G. Liu, S. C. Smith, H. M. Cheng and G. Q. Lu, Anatase TiO₂ single crystals with a large percentage of reactive facets, *Nature*, 2008, **453**(7195), 638–641.
- 4 Z. Sun, J. H. Kim, Y. Zhao, F. Bijarbooneh, V. Malgras, Y. Lee, Y.-M. Kang and S. X. Dou, Rational Design of 3D Dendritic TiO₂ Nanostructures with Favorable Architectures, *J. Am. Chem. Soc.*, 2011, **133**(48), 19314–19317.

- 5 H. Lin, L. Li, M. Zhao, X. Huang, X. Chen, G. Li and R. Yu, Synthesis of High-Quality Brookite TiO₂ Single-Crystalline Nanosheets with Specific Facets Exposed: Tuning Catalysts from Inert to Highly Reactive, *J. Am. Chem. Soc.*, 2012, **134**(20), 8328–8331.
- 6 Y. Liu, A. Tang, Q. Zhang and Y. Yin, Seed-Mediated Growth of Anatase TiO₂ Nanocrystals with Core-Antenna Structures for Enhanced Photocatalytic Activity, *J. Am. Chem. Soc.*, 2015, **137**(35), 11327–11339.
- 7 W. Zhou, W. Li, J.-Q. Wang, Y. Qu, Y. Yang, Y. Xie, K. Zhang, L. Wang, H. Fu and D. Zhao, Ordered Mesoporous Black TiO₂ as Highly Efficient Hydrogen Evolution Photocatalyst, *J. Am. Chem. Soc.*, 2014, **136**(26), 9280–9283.
- 8 P. Zhou, H. Zhang, H. Ji, W. Ma, C. Chen and J. Zhao, Modulating the photocatalytic redox preferences between anatase TiO₂ {001} and {101} surfaces, *Chem. Commun.*, 2017, **53**(4), 787–790.
- 9 Y. Liu, K. Lan, S. Li, Y. Liu, B. Kong, G. Wang, P. Zhang, R. Wang, H. He, Y. Ling, A. M. Al-Enizi, A. A. Elzatahry, Y. Cao, G. Chen and D. Zhao, Constructing Three-Dimensional Mesoporous Bouquet-Posy-like TiO₂ Superstructures with Radially Oriented Mesochannels and Single-Crystal Walls, *J. Am. Chem. Soc.*, 2017, **139**(1), 517–526.
- 10 C.-C. Wang and J. Y. Ying, Sol-Gel Synthesis and Hydrothermal Processing of Anatase and Rutile Titania Nanocrystals, *Chem. Mater.*, 1999, **11**(11), 3113–3120.
- 11 Y. Sang, B. Geng and J. Yang, Fabrication and growth mechanism of three-dimensional spherical TiO₂ architectures consisting of TiO₂ nanorods with {110} exposed facets, *Nanoscale*, 2010, **2**(10), 2109–2113.
- 12 K. Sabyrov, N. D. Burrows and R. L. Penn, Size-Dependent Anatase to Rutile Phase Transformation and Particle Growth, *Chem. Mater.*, 2012, **25**(8), 1408–1415.
- 13 H. Xu, S. Ouyang, P. Li, T. Kako and J. Ye, High-Active Anatase TiO₂ Nanosheets Exposed with 95% {100} Facets Toward Efficient H₂ Evolution and CO₂ Photoreduction, *ACS Appl. Mater. Interfaces*, 2013, **5**(4), 1348–1354.
- 14 Y. Yu and D. Xu, Single-crystalline TiO₂ nanorods: Highly active and easily recycled photocatalysts, *Appl. Catal., B*, 2007, **73**(1–2), 166–171.
- 15 Y. Mao and S. S. Wong, Size- and Shape-Dependent Transformation of Nanosized Titanate into Analogous Anatase Titania Nanostructures, *J. Am. Chem. Soc.*, 2006, **128**(25), 8217–8226.
- 16 D. Wu, Z. Gao, F. Xu, J. Chang, S. Gao and K. Jiang, Anatase TiO₂ nanocrystals enclosed by well-defined crystal facets and their application in dye-sensitized solar cell, *CrystEngComm*, 2013, **15**(3), 516–523.
- 17 H. Zhu, X. Gao, Y. Lan, D. Song, Y. Xi and J. Zhao, Hydrogen Titanate Nanofibers Covered with Anatase Nanocrystals: A Delicate Structure Achieved by the Wet Chemistry Reaction of the Titanate Nanofibers, *J. Am. Chem. Soc.*, 2004, **126**(27), 8380–8381.
- 18 H. Y. Zhu, Y. Lan, X. P. Gao, S. P. Ringer, Z. F. Zheng, D. Y. Song and J. C. Zhao, Phase Transition between Nanostructures of Titanate and Titanium Dioxides via Simple Wet-Chemical Reactions, *J. Am. Chem. Soc.*, 2005, **127**(18), 6730–6736.
- 19 P. Gao, D. Bao, Y. Wang, Y. Chen, L. Wang, S. Yang, G. Chen, G. Li, Y. Sun and W. Qin, Epitaxial Growth Route to Crystalline TiO₂ Nanobelts with Optimizable Electrochemical Performance, *ACS Appl. Mater. Interfaces*, 2012, **5**(2), 368–373.
- 20 H. Wang, H. Lin, Y. Long, B. Ni, T. He, S. Zhang, H. Zhu and X. Wang, Titanocene dichloride (Cp₂TiCl₂) as a precursor for template-free fabrication of hollow TiO₂ nanostructures with enhanced photocatalytic hydrogen production, *Nanoscale*, 2017, **9**(5), 2074–2081.
- 21 T. Ichijo, S. Sato and M. Fujita, Size-, Mass-, and Density-Controlled Preparation of TiO₂ Nanoparticles in a Spherical Coordination Template, *J. Am. Chem. Soc.*, 2013, **135**(18), 6786–6789.
- 22 J. Ye, W. Liu, J. Cai, S. Chen, X. Zhao, H. Zhou and L. Qi, Nanoporous Anatase TiO₂ Mesocrystals: Additive-Free Synthesis, Remarkable Crystalline-Phase Stability, and Improved Lithium Insertion Behavior, *J. Am. Chem. Soc.*, 2010, **133**(4), 933–940.
- 23 X. Jiang, T. Herricks and Y. Xia, Monodispersed Spherical Colloids of Titania: Synthesis, Characterization, and Crystallization, *Adv. Mater.*, 2003, **15**(14), 1205–1209.
- 24 X. Jiang, Y. Wang, T. Herricks and Y. Xia, Ethylene glycol-mediated synthesis of metal oxide nanowires, *J. Mater. Chem.*, 2004, **14**(4), 695–703.
- 25 L.-S. Zhong, J.-S. Hu, L.-J. Wan and W.-G. Song, Facile synthesis of nanoporous anatase spheres and their environmental applications, *Chem. Commun.*, 2008, (10), 1184–1186.
- 26 G. Cheng, M. S. Akhtar, O. B. Yang and F. J. Stadler, Novel preparation of anatase TiO₂@reduced graphene oxide hybrids for high-performance dye-sensitized solar cells, *ACS Appl. Mater. Interfaces*, 2013, **5**(14), 6635–6642.
- 27 G. Cheng and F. J. Stadler, Achieving phase transformation and structure control of crystalline anatase TiO₂@C hybrids from titanium glycolate precursor and glucose molecules, *J. Colloid Interface Sci.*, 2015, **438**, 169–178.
- 28 G. Cheng, F. Xu, J. Xiong, F. Tian, J. Ding, F. J. Stadler and R. Chen, Enhanced adsorption and photocatalysis capability of generally synthesized TiO₂-carbon materials hybrids, *Adv. Powder Technol.*, 2016, **27**(5), 1949–1962.
- 29 G. Cheng, M. S. Akhtar, O. B. Yang and F. J. Stadler, Structure modification of anatase TiO₂ nanomaterials-based photoanodes for efficient dye-sensitized solar cells, *Electrochim. Acta*, 2013, **113**, 527–535.
- 30 G. Cheng, F. Xu, J. Xiong, Y. Wei, F. J. Stadler and R. Chen, A novel protocol to design TiO₂-Fe₂O₃ hybrids with effective charge separation efficiency for improved photocatalysis, *Adv. Powder Technol.*, 2017, **28**(2), 665–670.
- 31 Y. Wei, G. Cheng, J. Xiong, F. Xu and R. Chen, Positive Ni (HCO₃)₂ as a novel cocatalyst for boosting photocatalytic hydrogen evolution capability of mesoporous TiO₂ nanocrystals, *ACS Sustainable Chem. Eng.*, 2017, **5**, 5027–5038.

- 32 N. Roy, Y. Sohn and D. Pradhan, Synergy of Low-Energy {101} and High-Energy {001} TiO₂ Crystal Facets for Enhanced Photocatalysis, *ACS Nano*, 2013, 7(3), 2532–2540.
- 33 T. A. Kandel, A. Feldhoff, L. Robben, R. Dillert and D. W. Bahnemann, Tailored Titanium Dioxide Nanomaterials: Anatase Nanoparticles and Brookite Nanorods as Highly Active Photocatalysts, *Chem. Mater.*, 2010, 22(6), 2050–2060.
- 34 M. Cargnello, T. R. Gordon and C. B. Murray, Solution-Phase Synthesis of Titanium Dioxide Nanoparticles and Nanocrystals, *Chem. Rev.*, 2014, 114(19), 9319–9345.
- 35 D. Reyes-Coronado, G. Rodríguez-Gattorno, M. E. Espinosa-Pesqueira, C. Cab, R. D. Coss and G. Oskam, Phase-pure TiO₂ nanoparticles: anatase, brookite and rutile, *Nanotechnology*, 2008, 19(14), 145605.
- 36 M. Zhao, L. Li, H. Lin, L. Yang and G. Li, A facile strategy to fabricate large-scale uniform brookite TiO₂ nanospindles with high thermal stability and superior electrical properties, *Chem. Commun.*, 2013, 49(63), 7046–7048.
- 37 Y. Xu, M. Kraft and R. Xu, Metal-free carbonaceous electrocatalysts and photocatalysts for water splitting, *Chem. Soc. Rev.*, 2016, 45(11), 3039–3052.
- 38 L. Li, S. Bai, W. Yin, S. Li, Y. Zhang and Z. Li, A novel etching and reconstruction route to ultrathin porous TiO₂ hollow spheres for enhanced photocatalytic hydrogen evolution, *Int. J. Hydrogen Energy*, 2016, 41(3), 1627–1634.
- 39 J. Jitputti, T. Rattanaoravipha, S. Chuangchote, S. Pavasupree, Y. Suzuki and S. Yoshikawa, Low temperature hydrothermal synthesis of monodispersed flower-like titanate nanosheets, *Catal. Commun.*, 2009, 10(4), 378–382.
- 40 J. Yu, Y. Hai and B. Cheng, Enhanced Photocatalytic H₂-Production Activity of TiO₂ by Ni(OH)₂ Cluster Modification, *J. Phys. Chem. C*, 2011, 115(11), 4953–4958.
- 41 X. Zou and Y. Zhang, Noble metal-free hydrogen evolution catalysts for water splitting, *Chem. Soc. Rev.*, 2015, 44(15), 5148–5180.
- 42 Q. Huang, S. Tian, D. Zeng, X. Wang, W. Song, Y. Li, W. Xiao and C. Xie, Enhanced Photocatalytic Activity of Chemically Bonded TiO₂/Graphene Composites Based on the Effective Interfacial Charge Transfer through the C–Ti Bond, *ACS Catal.*, 2013, 3(7), 1477–1485.
- 43 P. Zhang, T. Wang, X. Chang and J. Gong, Effective Charge Carrier Utilization in Photocatalytic Conversions, *Acc. Chem. Res.*, 2016, 49(5), 911–921.
- 44 A. Tanaka, K. Teramura, S. Hosokawa, H. Kominami and T. Tanaka, Visible light-induced water splitting in an aqueous suspension of a plasmonic Au/TiO₂ photocatalyst with metal co-catalysts, *Chem. Sci.*, 2017, 8(4), 2574–2580.
- 45 J. Low, J. Yu, M. Jaroniec, S. Wageh and A. A. Al-Ghamdi, Heterojunction Photocatalysts, *Adv. Mater.*, 2017, 29(20), 1601694.
- 46 K. Li, B. Peng and T. Peng, Recent Advances in Heterogeneous Photocatalytic CO₂ Conversion to Solar Fuels, *ACS Catal.*, 2016, 6(11), 7485–7527.
- 47 A. Migani and L. Blancafort, Excitonic Interfacial Proton-Coupled Electron Transfer Mechanism in the Photocatalytic Oxidation of Methanol to Formaldehyde on TiO₂(110), *J. Am. Chem. Soc.*, 2016, 138(49), 16165–16173.
- 48 M. Nolan, A. Iwaszuk, A. K. Lucid, J. J. Carey and M. Fronzi, Design of Novel Visible Light Active Photocatalyst Materials: Surface Modified TiO₂, *Adv. Mater.*, 2016, 28(27), 5425–5446.