University of Wollongong

Research Online

Faculty of Engineering and Information
Sciences - Papers: Part A

Faculty of Engineering and Information
Sciences

1-1-2016

Design-oriented stress–strain model for concrete under combined FRP- steel confinement

G Lin

Hong Kong Polytechnic University

Tao Yu

University of Wollongong, taoy@uow.edu.au

Jin Guang Teng

Hong Kong Polytechnic University, cejgteng@polyu.edu.hk

Follow this and additional works at: <https://ro.uow.edu.au/eispapers>

Part of the [Engineering Commons](#), and the [Science and Technology Studies Commons](#)

Research Online is the open access institutional repository for the University of Wollongong. For further information contact the UOW Library: research-pubs@uow.edu.au

Design-oriented stress–strain model for concrete under combined FRP-steel confinement

Abstract

Extensive research has been conducted on fiber-reinforced polymer (FRP)-confined plain and RC columns, leading to a large number of stress–strain models. Most of these models have been developed for FRP-confined plain concrete and are thus applicable only to concrete in FRP-confined RC columns with a negligible amount of transverse steel reinforcement. The few models that have been developed for concrete under the combined confinement of FRP and transverse steel reinforcement are either inaccurate or too complex for direct use in design. This paper presents an accurate design-oriented stress–strain model for concrete under combined FRP-steel confinement in FRP-confined circular RC columns. The proposed model is formulated on the basis of extensive numerical results generated using an analysis-oriented stress–strain model recently proposed by the authors and properly captures the key characteristics of FRP-steel-confined concrete as revealed by existing test results. The model strikes a good balance between accuracy of prediction and simplicity of form and is shown to provide close predictions of test results and perform significantly better than existing stress–strain models of the same type.

Keywords

stress, strain, model, concrete, design, under, oriented, combined, frp, steel, confinement

Disciplines

Engineering | Science and Technology Studies

Publication Details

Lin, G., Yu, T. & Teng, J. G. (2016). Design-oriented stress–strain model for concrete under combined FRP-steel confinement. *Journal of Composites for Construction*, 20 (4), 04015084-1-04015084-11.

DESIGN-ORIENTED STRESS-STRAIN MODELS FOR CONCRETE UNDER COMBINED FRP-STEEL CONFINEMENT

G. Lin¹, T. Yu² and J.G. Teng³

Abstract: Extensive research has been conducted on FRP-confined plain and reinforced concrete (RC) columns, leading to a large number of stress-strain models. Most of these models have been developed for FRP-confined plain concrete and are thus applicable only to concrete in FRP-confined RC columns with a negligible amount of transverse steel reinforcement. The few models that have been developed for concrete under the combined confinement of FRP and transverse steel reinforcement are either inaccurate or too complex for direct use in design. This paper presents an accurate design-oriented stress-strain model for concrete under combined FRP-steel confinement in FRP-confined circular RC columns. The proposed model is formulated on the basis of extensive numerical results generated using an analysis-oriented stress-strain model recently proposed by the authors and properly captures the key characteristics of FRP-steel-confined concrete as revealed by existing test results. The model strikes a good balance between accuracy of prediction and simplicity in form and is shown to provide close predictions of test results and perform significantly better than existing stress-strain models of the same type.

Keywords: RC column; Fiber reinforced polymer (FRP); Stress-strain model; Design; Confinement; Transverse steel reinforcement

INTRODUCTION

In the past two decades, fibre-reinforced polymer (FRP) has emerged as a popular confining material for the strengthening of existing concrete columns (Teng *et al.* 2002; Hollaway and Teng 2008). As a result, extensive research has been devoted to the behavior and modelling of FRP-confined concrete (FCC), mostly through axial compression tests on short FRP-confined plain concrete columns. The vast majority of the existing studies have been concerned with circular concrete columns under axial compression, in which the concrete is uniformly confined. Similarly, the scope of the present paper is limited to circular FRP-confined plain or reinforced concrete (RC) columns under axial compression.

As far as circular columns are concerned, the results of axial compression tests on short FRP-confined plain concrete columns can now be closely predicted by some of the existing stress-strain models such as those proposed by Jiang and Teng (2007) and Teng *et al.* (2009). These stress-strain models, however, cannot be directly used in predicting the behavior of FRP-confined RC columns (referred to as FCRC columns hereafter) when the column is provided with a significant amount of transverse steel reinforcement (TSR). In FCRC columns, the core concrete is subjected to combined

¹ PhD Candidate, Department of Civil and Environmental Engineering, The Hong Kong Polytechnic University, Hong Kong, China.

² Senior Lecturer, School of Civil, Mining and Environmental Engineering, Faculty of Engineering and Information Sciences, University of Wollongong, Northfields Avenue, Wollongong, NSW 2522, Australia.

³ Chair Professor of Structural Engineering, Department of Civil and Environmental Engineering, The Hong Kong Polytechnic University, Hong Kong, China (Corresponding author). Email: cejgteng@polyu.edu.hk

confinement from the FRP jacket and the TSR, and is referred to as FRP-steel-confined concrete (FSCC) hereafter.

The behavior of FSCC has received increasing research attention in recent years (Demers and Neale 1999; Pessiki *et al.* 2001; Li *et al.* 2003; Lin and Liao 2004; Carey and Harries 2005; Esfahani and Kianoush 2005; Matthys *et al.* 2005; Rocca 2007; Ilki *et al.* 2008; Eid *et al.* 2009; Chastre and Silva 2010; Lee *et al.* 2010; Wang *et al.* 2012; Zhang 2012), leading to several stress-strain models. Similar to those for FCC (Teng and Lam 2004), the existing stress-strain models for FSCC can be classified into two main categories: design-oriented models in closed-form expressions (e.g., Eid and Paultre 2008; Chastre and Silva 2010; Lee *et al.* 2010; Pellegrino and Modena 2010; Wang *et al.* 2012; Shirmohammadi *et al.* 2015) and analysis-oriented models which predict stress-strain curves using an incremental procedure (e.g., Braga *et al.* 2006; Megalooikonomou *et al.* 2012; Hu and Seracino 2013). Compared with analysis-oriented models, design-oriented models are particularly suitable for direct application in design calculations. By contrast, analysis-oriented models, which account explicitly for the interaction between the confining material(s) and the concrete, are more versatile and may be used to gain a better understanding of behavior and to generate numerical results for the development of a design-oriented model (Teng *et al.* 2009). Existing design-oriented stress-strain models for FSCC have generally been established based on the interpretation of limited experimental results available to the researchers at the time of their study. The accuracy of these models therefore depends greatly on the quality and extensiveness of the test database employed.

The present paper is concerned with the development of a new design-oriented stress-strain model for FSCC using a different methodology. This new design-oriented model is based on extensive numerical results from an accurate analysis-oriented model recently proposed by the authors (Teng *et al.* 2014). Teng *et al.*'s (2014) model is within the framework of Jiang and Teng's (2007) model for FCC but includes necessary revisions to account for the effect of TSR. With Teng *et al.*'s (2014) model, the stress-strain curve is generated via an incremental process that makes use of a series of stress-strain curves of actively-confined concrete at different confining pressures (Teng *et al.* 2014). Teng *et al.*'s (2014) model has been verified against a large test database and has been shown to be superior to other existing stress-strain models of the same category (i.e., Braga *et al.* 2006; Megalooikonomou *et al.* 2012; Hu and Seracino 2013) in terms of both rationality and accuracy. A similar approach has previously been employed by Teng *et al.* (2009) to develop a design-oriented stress-strain model for FCC (i.e., concrete confined with FRP only).

The paper begins with a description of the stress-strain behavior of FSCC as revealed by existing test results, based on which algebraic expressions for a three-segment stress-strain model is proposed. The definitions of key parameters in the proposed model are then developed on the basis of regression analyses of numerical results obtained from Teng *et al.*'s (2014) analysis-oriented model. Finally, the performance of the proposed model is verified against a large test database and compared with existing design-oriented stress-strain models.

It should be noted that in this paper, the term "stress-strain" represents "axial stress-axial strain" unless otherwise specified. The following sign convention is adopted: in the axial direction, compressive stresses and strains are positive but in the hoop direction, tensile stresses and strains are positive.

Figure 1 shows two typical stress-strain curves of FSCC generated using Teng *et al.*'s (2014) analysis-oriented model; the curves of the corresponding FCC and steel-confined concrete (SCC) (i.e., concrete confined with steel only) generated using the same model are also shown for comparison. Figure 1(a) is for a case where the FRP jacket is relatively flexible, while Figure 1(b) is for a case with a relatively stiff FRP jacket. Figure 1(a) shows that the curve of FSCC is very close to that of the corresponding SCC when the FRP jacket is relatively flexible. In this case, the stress-strain behavior of FSCC can be closely and conservatively predicted by an existing stress-strain model for SCC, with the contribution of FRP being ignored. Therefore, this paper is concerned mainly with cases similar to that shown in Figure 1(b) where a relatively stiff FRP jacket leads to an FSCC curve which is significantly higher than that of the corresponding SCC. With the relatively stiff FRP jacket, the curve of FCC shows a monotonically increasing bilinear shape [Figure 1(b)], which has been well established by existing research on FCC (e.g., Lam and Teng 2003; Teng *et al.* 2009). The threshold of FRP jacket stiffness to ensure such a bilinear stress-strain curve of FCC has been investigated by many researchers, and the following equation for the confinement stiffness ratio (ρ_k) was proposed by Teng *et al.* (2009) for their model:

$$\rho_k = \frac{2E_f t_f}{D(f'_{co}/\epsilon_{co})} \geq 0.01 \quad (1)$$

where E_f and t_f are the elastic modulus and the thickness of the FRP jacket respectively; D is the diameter of the column section; f'_{co} and ϵ_{co} are the compressive strength of unconfined concrete and the corresponding strain respectively. Eq. (1) is also adopted in the present study as the definition of a sufficiently stiff FRP jacket for FSCC. In the subsequent sections, FSCC refers to FSCC with a ρ_k value not smaller than 0.01 unless otherwise specified.

It is evident from Figure 1(b) that the stress-strain curve of FSCC possesses the following characteristics: (1) it consists of two approximately linear portions connected by a curved transition portion; (2) the transition portion is significantly longer than that of the corresponding FCC; (3) the second linear portion is higher than and approximately parallel to that of the FCC. These characteristics have also been well established by the existing experimental results (Teng *et al.* 2014). Because of the existence of a much longer transition portion, the form of expressions used in existing design-oriented stress-strain models for FCC may not be suitable for FSCC. The expressions of Lam and Teng's stress-strain model for FCC (Lam and Teng 2003; Teng *et al.* 2009) are employed here to clarify this point. These expressions have been adopted in various design codes/guidelines, including the relevant Chinese standard (GB50608 2010) and the relevant design guidelines developed by the American Concrete Institute [ACI 440-08 (2008)] and the UK Concrete Society (2012). Lam and Teng's (2003) model consists of a parabolic first segment and a linear second segment, and is given by the following expressions:

$$\sigma_c = \begin{cases} E_c \epsilon_c - \frac{(E_c - E_2)^2}{4f_i} \epsilon_c^2 & 0 \leq \epsilon_c < \epsilon_{tf} \\ f_i + E_2 \epsilon_c & \epsilon_{tf} \leq \epsilon_c \leq \epsilon_{cu} \end{cases} \quad (2)$$

where σ_c and ϵ_c are the axial stress and strain of concrete respectively; E_c is the

elastic modulus of concrete; E_2 is the slope of the linear second segment of the stress-strain curve; f_i is the intercept of the stress axis by the linear second segment (referred to as the intercept stress hereafter); and ε_{tf} and f_{tf} are the transition strain and stress for FCC respectively.

With Lam and Teng's model, the linear second segment (i.e., a two-parameter function) is uniquely defined by the slope E_2 and the ultimate state ($\varepsilon_{cu}, f'_{cu}$); the parabolic first segment (i.e., a three-parameter function) as well as the transition strain and stress is uniquely defined by E_c , the condition that the two segments connect smoothly, and the implied condition that the curve passes through the origin. In Figure 2, a typical stress-strain curve of FSCC from Wang *et al.*'s (2012) tests is compared with the corresponding curve generated by Lam and Teng's model using the experimental values for E_2 , E_c and the ultimate state ($\varepsilon_{cu}, f'_{cu}$). It is evident from Figure 2 that a significant discrepancy exists between the two curves in the transition zone despite the good agreement of the two in terms of other parts; the strain at the starting point of the second linear portion (i.e., the transition strain) of FSCC is also seen to be significantly larger than that on the curve generated by Lam and Teng's model. It should be noted that when stress-strain curves for FSCC are discussed elsewhere in the paper, the term "transition strain" is reserved for the starting point of the second linear portion (i.e., referred to as "segment" in the models) for simplicity of presentation although another transition strain exists between the first linear portion and the curved transition portion when the whole stress-strain curve is modelled as three segments. Apparently, the expressions adopted by Lam and Teng's model cannot provide close predictions for FSCC.

PROPOSED STRESS-STRAIN MODEL FOR FSCC

Algebraic Expressions for Stress-Strain Curves

As shown in Figure 1(b), the stress-strain curve of FSCC generally consists of two approximately linear portions connected by a curved transition portion. A review of the existing stress-strain models for FSCC reveals that these models can be classified into three categories: single-segment models which use a single expression to describe the entire stress-strain curve (e.g., Chastre and Silva 2010; Pellegrino and Modena 2010; Wang *et al.* 2012; Shirmohammadi *et al.* 2015), two-segment models which consist of two segments defined by two separate expressions (e.g., Li *et al.* 2003; Harajli 2006; Eid and Paultre 2008) and three-segment models which consist of three segments defined by three separate expressions (e.g., Lee *et al.* 2010). Lin *et al.* (2015) examined the algebraic expressions of existing models, and explored four different options for representing the stress-strain curve of FSCC based on the test results collected by them. Among the four options, the following three-segment option, which strikes a good balance between accuracy of prediction and simplicity in form, is adopted in the present study. The stress-strain curve defined by the three-segment option consists of two linear segments connected by a curved transition segment (Figure 3) which is described by a four-parameter n th-order expression. The four-parameter expression allows the use of a predefined transition strain in determining the parameters. The three-segment model is expressed by:

$$\sigma_c = \begin{cases} E_c \varepsilon_c & \text{for } 0 \leq \varepsilon_c < \varepsilon_0 \\ f_0 + E_c (\varepsilon_c - \varepsilon_0) + a (\varepsilon_c - \varepsilon_0)^n & \text{for } \varepsilon_0 \leq \varepsilon_c < \varepsilon_t \\ f_t + E_2 (\varepsilon_c - \varepsilon_t) & \text{for } \varepsilon_t \leq \varepsilon_c \leq \varepsilon_{cu} \end{cases} \quad (3)$$

where ε_0 and f_0 are the strain and the stress of the termination point of the first linear segment; a and n are constants and can be determined with the condition that the second segment and the third segment (also referred to as the second linear segment or final segment in the paper) are smoothly connected at the transition point (ε_t, f_t) :

$$n = \frac{E_2 - E_c}{E_{\text{sec}} - E_c} \quad (4)$$

$$a = \frac{E_{\text{sec}} - E_c}{(\varepsilon_t - \varepsilon_0)^{(n-1)}} \quad (5)$$

$$E_{\text{sec}} = \frac{f_t - f_0}{\varepsilon_t - \varepsilon_0} \quad (6)$$

The termination point of the first linear segment (ε_0, f_0) is defined to be at the stress level of $\Delta f'_{cs}$ so that this model reduces to Lam and Teng's (2003) model when there is no TSR (i.e., $\Delta f'_{cs} = 0$). That is,

$$f_0 = \Delta f'_{cs} \quad (7)$$

$$\varepsilon_0 = f_0 / E_c \quad (8)$$

There are five independent parameters in the three-segment model (i.e., E_2 , E_c , f_i , ε_t , and ε_{cu}), while the transition stress, f_t , can be found from $f_t = f_i + E_2 \varepsilon_t$. Among the five independent parameters, E_c can be obtained from $E_c = 4730 \sqrt{f'_{co}}$ (f'_{co} in MPa) following ACI 318-08 (2008); f_i is generally taken to be equal to f'_{co} for FCC (Lam and Teng 2003), and can thus be calculated as $f_i = f'_{co} + \Delta f'_{cs}$ with $\Delta f'_{cs}$ being used to account for the increase of intercept stress due to confinement from TSR. The remaining three parameters, E_2 , ε_t , and ε_{cu} , as well as $\Delta f'_{cs}$, need to be found from regression analyses of numerical results generated using Teng *et al.*'s (2014) analysis-oriented model and are discussed later in this paper. It should be noted that the slope of the second linear segment (i.e., the final-segment slope) in the present three-segment model (denoted by E_2) corresponds to that of the second segment in Lam and Teng's (2003) model for FCC.

Final-Segment Slope E_2

As discussed earlier, the second linear portion of the stress-strain curve of FSCC is approximately parallel to that of the corresponding FCC (Figure 1). Therefore, an equation capable of close predictions for the final-segment slope (E_2) of FCC is expected to also provide close predictions for that of FSCC. In the present study, a parametric study (i.e., Parametric Study 1) was conducted using Teng *et al.*'s (2014)

model on FCC to generate numerical results to derive such a predictive equation. Teng *et al.*'s (2014) model reduces to Jiang and Teng's (2007) model for FCC when there is no TSR. The main parameters considered in the parametric study included the unconfined concrete strength (f'_{co}), the confinement stiffness ratio of FRP (ρ_K), and the rupture strain of FRP ($\epsilon_{h,rupt}$). The ranges of these parameters in the parametric study were selected with reference to values commonly found in laboratory tests and practical cases, which are summarized in Table 1. In the parametric study, it was assumed $\epsilon_{co} = 9.37 \times 10^{-4} \sqrt[4]{f'_{co}}$ (f'_{co} in MPa) (Popovics 1973) and $E_c = 4730 \sqrt{f'_{co}}$ (f'_{co} in MPa) (ACI 318-08 2008). The final-segment slope (E_2) was obtained from each stress-strain curve generated in the parametric study in the following way: (1) assume that the intercept stress is equal to f'_{co} following Lam and Teng (2003); (2) obtain the stress and strain at the ultimate state from the curve; (3) calculate E_2 as the slope of the straight line connecting the point of ultimate state and the point of intercept stress ($0, f'_{co}$). Similar to the findings from numerous experimental and theoretical studies (e.g., Samaan *et al.* 1998; Xiao and Wu 2000; Fahmy and Wu 2010), results from the parametric study showed that the final-segment slope (E_2) depends greatly on the FRP confinement stiffness ratio (ρ_K) (Figure 4). The following expression is therefore proposed for E_2 for both FCC and FSCC based on a regression analysis of the results from the parametric study:

$$\frac{E_2}{f'_{co}} = 29.9 \ln(\rho_K) + 134 \quad (9)$$

With Eq. (9), the threshold of ρ_K for a positive E_2 can be obtained to be 0.0113, which is approximately the same as that proposed by Teng *et al.* (2009) [i.e., Eq. (1)].

Increase of Intercept Stress due to TSR

Another parametric study (i.e., Parametric Study 2) was conducted to obtain a predictive equation for the increase of intercept stress due to confinement from TSR (i.e., $\Delta f'_{cs}$ in

Figure 3). It should be noted that $\Delta f'_{cs}$ is different from $\Delta f'_{cc,s}$ in Teng *et al.*'s (2014) model, where the latter represents the TSR contribution to the peak axial stress in the stress-strain model for active confinement adopted by Teng *et al.* (2014). The main parameters considered in the parametric study included the effective steel confinement stiffness (K_{steel}) and the yield stress of the steel spiral/hoops (f_{yh}) besides the three parameters adopted in Parametric Study 1, based on the findings from Teng *et al.* (2014). Following Mander *et al.* (1988) and Teng *et al.* (2014), the effective steel confinement stiffness (K_{steel}) is defined by:

$$K_{steel} = \frac{2k_e E_s A_s}{s d_s} \quad (10)$$

where E_s , f_{yh} , and A_s are the elastic modulus, yield stress, and cross-sectional area of a steel spiral/hoop respectively; s is the vertical center-to-center spacing of steel hoops or spirals; d_s is the diameter of center line of steel spirals/hoops; and k_e is the confinement effectiveness coefficient to account for confinement non-uniformity over the column height and is defined as follows:

$$k_e = \begin{cases} \left(1 - \frac{s'}{2d_s}\right)^2 / (1 - \rho_{cc}) & \text{for circular hoops} \\ \left(1 - \frac{s'}{2d_s}\right) / (1 - \rho_{cc}) & \text{for circular spirals} \end{cases} \quad (11)$$

where s' is the clear vertical spacing of steel spirals/hoops ($s' = s - d_s$) and ρ_{cc} is the ratio of cross-sectional area between the longitudinal steel reinforcement and the enclosed concrete core.

With the definition of K_{steel} , the effective confining pressure from TSR after the yielding of TSR can be calculated as

$$f'_{ls,y} = K_{steel} \epsilon_y = \frac{K_{steel} f_{yh}}{E_s} \quad (12)$$

where ϵ_y is the yield strain of steel spirals/hoops.

The ranges for the parameters covered in the parametric study are also summarized in Table 1. The increase of intercept stress due to confinement from TSR (i.e., $\Delta f'_{cs}$) was obtained from each stress-strain curve generated in the parametric study in the following way: (1) obtain the stress and strain at the ultimate state from the curve; (2) obtain the intercept stress, f'_i , as the intercept of the stress axis by the straight line which has a slope of E_2 calculated from Eq. (9) and passes through the point of ultimate state; (3) find $\Delta f'_{cs}$ by $\Delta f'_{cs} = f'_i - f'_{co}$. It should be noted that although most of the stress-strain curves generated in the parametric study have a shape similar to that shown in Figure 1(b), a small fraction of the curves does not have the linear final portion (Figure 5). This happens when the confinement from the TSR is very low and/or the rupture strain of FRP is relatively small so that the ultimate state (i.e., FRP rupture) is reached before the yielding of TSR. These curves were identified by comparing the slope of the stress-strain curve at the ultimate state and the E_2 value of the corresponding FCC, and were excluded when calculating $\Delta f'_{cs}$.

The results from the parametric study indicate that $\Delta f'_{cs}$ depends greatly on the effective steel confinement ratio ($f'_{ls,y} / f'_{co}$) and the confinement stiffness ratio between FRP and TSR ($\rho_f = K_{frp} / K_{steel}$). To propose a rational expression for $\Delta f'_{cs}$, the following two extreme conditions were considered: (1) when no TSR is present, $\Delta f'_{cs}$ should be equal to zero; (2) as $\Delta f'_{cs}$ basically represents the increase of strength due to confinement of TSR, its expression may be so selected that it reduces to an accurate existing equation for the peak stress of SCC when there is no FRP jacket (i.e., $\rho_f = 0$). Given the above considerations, the following equation is proposed:

$$\frac{\Delta f'_{cs}}{f'_{co}} = 3.12 \left[\frac{f'_{ls,y}}{f'_{co} (1 + a \rho_f^b)} \right]^{0.736} \quad (13)$$

Eq. (13) provides accurate predictions of the axial stress of SCC when $\rho_f = 0$ (Teng et al. 2014). A regression analysis was conducted to minimize the errors between the predictions of Eq. (13) and the results from the parametric study (i.e., Parametric Study

2), leading to $a = 7.07$ and $b = 1.60$ (Figure 6). Eq. (13) thus becomes:

$$\frac{\Delta f'_{cs}}{f'_{co}} = 3.12 \left[\frac{f'_{ls,y}}{f'_{co} (1 + 7.07 \rho_f^{1.60})} \right]^{0.736} \quad (14)$$

Transition Strain

The transition strain (ϵ_t) is the strain at the starting point of the second linear portion of the stress-strain curve of FSCC. The second linear portion is governed mostly by the confinement stiffness of FRP, which means that the confinement effect of TSR becomes negligible after the transition strain. Therefore, it is reasonable to expect that the transition strain is approximately equal to the strain at the peak stress of SCC (ϵ_{cc}) when the confinement stiffness of FRP is not too large. This is also evident from the experimental results from a number of studies on FSCC (Carey and Harries 2005; Matthys *et al.* 2005; Eid *et al.* 2009; Chastre and Silva 2010; Wang *et al.* 2012). The strain at the peak stress of SCC (ϵ_{cc}) can be predicted by a model for actively confined concrete (which can closely approximate the response of SCC after the yielding of TSR) such as the model proposed by Jiang and Teng (2007):

$$\frac{\epsilon_{cc}}{\epsilon_{co}} = 1 + 3.89 \left(\frac{f'_{cc}}{f'_{co}} - 1 \right)^{1.2} \quad (15)$$

where f'_{cc} is the peak stress of SCC.

In addition, the transition strain of FSCC should reduce to that of FCC when there is no TSR. Based on these considerations, the following equation is proposed for the transition strain (ϵ_t) of FSCC:

$$\frac{\epsilon_t}{\epsilon_{tf}} = 1 + 3.89 \left(\frac{\Delta f'_{cs}}{f'_{co}} \right)^{1.2} \quad (16)$$

where

$$\epsilon_{tf} = \frac{2f'_{co}}{E_c - E_2} \quad (17)$$

Eq. (16) means that ϵ_t is equal to the transition strain of FCC, ϵ_{tf} , when there is no TSR ($\Delta f'_{cs}$ is equal to zero) and the transition strain ϵ_t increases with the confinement stiffness of FRP, which is consistent with the test results of FSCC (e.g., Eid *et al.* 2009; Wang *et al.* 2012). Moreover, as ϵ_{tf} is very close to ϵ_{co} when the confinement stiffness of FRP is not too large, Eq. (16) implies that ϵ_t is approximately equal to ϵ_{cc} in Eq. (15).

Ultimate State

The ultimate state of FSCC is reached when the FRP jacket ruptures due to hoop tension (i.e., when the hoop strain of FRP reaches its rupture strain). Teng *et al.* (2014) proposed the following axial strain-FRP hoop strain relationship for FSCC:

$$\frac{\epsilon_c}{\epsilon_{co}} = 0.85 \left(1 + 8 \frac{f_{lf}}{f'_{co}} + \alpha \frac{f'_{ls}}{f'_{co}} \right) \left\{ \left[1 + 0.75 \left(\frac{\epsilon_h}{\epsilon_{co}} \right) \right]^{0.7} - \exp \left[-7 \left(\frac{\epsilon_h}{\epsilon_{co}} \right) \right] \right\} \quad (18)$$

$$\alpha = 1.59 + 15.1 \rho_f \quad (19)$$

329

330 With this relationship, the ultimate strain of FSCC (ϵ_{cu}) can be calculated by equating
331 the FRP hoop strain (ϵ_h) to the hoop rupture strain of FRP ($\epsilon_{h,rupt}$):

$$\frac{\epsilon_{cu}}{\epsilon_{co}} = 0.85 \left(1 + 8 \frac{f_{lf,rupt}}{f'_{co}} + \alpha \frac{f'_{ls,rupt}}{f'_{co}} \right) \left\{ \left[1 + 0.75 \left(\frac{\epsilon_{h,rupt}}{\epsilon_{co}} \right) \right]^{0.7} - \exp \left[-7 \left(\frac{\epsilon_{h,rupt}}{\epsilon_{co}} \right) \right] \right\} \quad (20)$$

333 where $f_{lf,rupt}$ and $f'_{ls,rupt}$ are the confining pressures from FRP and TSR at the ultimate
334 state respectively. $f'_{ls,rupt}$ can in principle be replaced by $f'_{ls,y}$ as long as the yield
335 strain of TSR is smaller than the hoop rupture strain of the FRP jacket.

336

337 Eq. (20), however, is too complex for direct use in practical design. To simplify Eq.
338 (33), the expression within the curly bracket on the right side of this equation is shown
339 against $\epsilon_{h,rupt} / \epsilon_{co}$ in Figure 7. It is evident from Figure 7 that the curve becomes
340 almost linear when $\epsilon_{h,rupt} / \epsilon_{co}$ exceeds around 0.5 (or when $\epsilon_{h,rupt}$ exceeds around
341 0.1%). This observation allows the use of a linear function to replace the complex
342 expression within the curly bracket, considering that the rupture strain of commonly
343 used FRP (e.g., carbon FRP and glass FRP) is much larger than 0.1%. The following
344 equation is therefore proposed to replace Eq. (33):

$$\frac{\epsilon_{cu}}{\epsilon_{co}} = 0.85 \left(1 + 8 \frac{f_{lf,rupt}}{f'_{co}} + \alpha \frac{f'_{ls,y}}{f'_{co}} \right) \left[1 + 0.465 \left(\frac{\epsilon_{h,rupt}}{\epsilon_{co}} \right) \right] \quad (21)$$

346

347 Eq. (21) can be rewritten as:

$$\frac{\epsilon_{cu}}{\epsilon_{co}} = \phi(f_{lf,rupt}, \epsilon_{h,rupt}) + 0.85 \alpha \frac{f'_{ls,y}}{f'_{co}} (1 + 0.465 \rho_\epsilon) \quad (22)$$

349 where $\phi(f_{lf,rupt}, \epsilon_{h,rupt})$ is a function of $f_{lf,rupt}$ and $\epsilon_{h,rupt}$. Apparently, Eq. (22) reduces
350 to the following equation for FCC:

$$\frac{\epsilon_{cu}}{\epsilon_{co}} = \phi(f_{lf,rupt}, \epsilon_{h,rupt}) \quad (23)$$

352

353 To retain consistency with the equation proposed by Teng *et al.* (2009) for the ultimate
354 strain of FCC, $\phi(f_{lf,rupt}, \epsilon_{h,rupt})$ is replaced by the corresponding expression in Teng *et*
355 *al.*'s (2009) model, and Eq. (22) becomes:

$$\frac{\epsilon_{cu}}{\epsilon_{co}} = 1.75 + 6.5 \rho_K^{0.80} \rho_\epsilon^{1.45} + 0.85 \alpha \frac{f'_{ls,y}}{f'_{co}} (1 + 0.465 \rho_\epsilon) \quad (24)$$

357

358 The predictions of Eq. (24) are compared with those of Eq. (20) in Figure 8 for all the
359 numerical cases in Table 1; close agreement can be seen between the two.

360

361 The ultimate strain ϵ_{cu} is normally larger than the transition strain ϵ_t calculated by
362 Eq.(16), except for cases where the confinement from TSR is very high and/or the
363 rupture strain of FRP is relatively small (Figure 5).

365 Summary of the Proposed Model

366 When $\varepsilon_{cu} > \varepsilon_t$, Eqs. (9), (14), (16), and (24), which are for E_2 , $\Delta f'_{cs}$, ε_t and ε_{cu}
 367 respectively, can be employed together with Eq. (3) to define the proposed model to
 368 predict the stress-strain response. In the rare case where $\varepsilon_{cu} \leq \varepsilon_t$, the final segment
 369 does not exist, so the proposed model only has two segments (i.e., the first two
 370 segments) with the second one terminating at a strain of ε_{cu} . Nevertheless, for the
 371 latter case, Eqs. (9) and (14) for E_2 and $\Delta f'_{cs}$ still need to be used to define the virtual
 372 final segment so that f_t can be found and used together with ε_t to define the first
 373 segment or the first two segments. The ultimate stress f'_{cu} can be easily found from
 374 ε_{cu} .

375
 376 It should also be noted that the proposed model is different from most existing
 377 stress-strain models (e.g., Lam and Teng 2003; Teng *et al.* 2009) for FCC or FSCC in
 378 the determination of E_2 . In the existing models (e.g., Lam and Teng 2003; Teng *et al.*
 379 2009), E_2 is calculated using the point of ultimate state (ε_{cu} , f'_{cu}) and the point of
 380 intercept stress (0, f_t). The main disadvantage of such models is that they predict
 381 different stress-strain paths for the same concrete confined with an FRP jacket of the
 382 same hoop stiffness but different FRP rupture strains ($\varepsilon_{h,rupt}$). Although these
 383 differences are small in practical cases, they are conceptually in disagreement with the
 384 understanding that the stiffness instead of the hoop rupture strain of the FRP jacket
 385 determines the stress-strain path. The advantage of such models is that they provide an
 386 explicit definition of the ultimate state, which is convenient in section analysis and
 387 member design. The proposed stress-strain model overcomes this drawback by
 388 ensuring that E_2 of the stress-strain curve is directly related to the stiffness of the FRP
 389 jacket. The proposed stress-strain model therefore may be referred to as a
 390 stiffness-based stress-strain model which is superior in cases where the correct
 391 prediction of stress-strain paths is of greater importance (e.g., seismic response
 392 analysis).

393 PERFORMANCE OF THE PROPOSED MODEL

394 Test Database

395 The test database of the present study consists of 48 FCRC specimens. It includes all
 396 the test data collected by Teng *et al.* (2014) from the studies of Demers and Neale
 397 (1999), Pessiki *et al.* (2001), Eid *et al.* (2009), Chastre and Silva (2010), Wang *et al.*
 398 (2012) and Zhang (2012), and results of another 5 FCRC specimens tested by Matthys
 399 *et al.* (2005). The 5 FCRC specimens of Matthys *et al.* (2005) had a diameter of 400
 400 mm and covered the ranges of parameters as follows: $f'_{co} = 29.2 \sim 33.4 \text{ MPa}$,
 401 $f'_{ls,y}/f'_{co} = 0.0225 \sim 0.0258$, $K_{steel}/f'_{co} = 8.03 \sim 9.20$, $\rho_K = 0.0121 \sim 0.149$,
 402 $\rho_\varepsilon = 1.15 \sim 3.33$. Matthys *et al.* (2005) provided only the axial stress-axial strain
 403 curves of these specimens (i.e., no axial stress-lateral strain curves), so they were not
 404 included in Teng *et al.*'s (2014) database. All the FRP-confined specimens were
 405 wrapped with an FRP jacket with fibers oriented in the hoop direction only via a wet
 406 lay-up process; 13 specimens tested by Eid *et al.* (2009) were reinforced with steel

spirals while the other specimens were reinforced with steel hoops.

The majority of the specimens in the database are medium- to large-scale specimens with the diameter being not smaller than 250 mm (up to 508 mm). It has been widely reported that the unconfined strength of concrete (f'_{co}) in columns of such a scale may be significantly lower than that found from standard concrete cylinder tests (i.e., f'_c) using 150mm $\times$ 300 mm cylinders, although the difference between f'_{co} and f'_c varies and is somewhat uncertain (Park and Paulay 1975; Demers and Neale 1999; Chastre and Silva 2010; De Luca *et al.* 2010; Zhang 2012). In the present study, f'_{co} is taken to be $0.85 f'_c$ following ACI 318 (2008) for all the specimens except the specimens presented in Pessiki *et al.* (2001), Chastre and Silva (2010) and Wang *et al.* (2012) where FCC columns with the same dimensions as the corresponding FCRC columns were tested; for these specimens, f'_{co} was back-calculated from the test results of FCC columns using Jiang and Teng's (2007) model. The same method of determining f'_{co} has also been adopted by Teng *et al.* (2014) and other researchers (e.g., Saatcioglu and Razvi 1992).

Increase of Intercept Stress due to TSR $\Delta f'_{cs}$

The experimental value of $\Delta f'_{cs}$ can be obtained as $\Delta f'_{cs} = f_i - f'_{co}$, where the intercept stress f_i can be extracted from the experimental stress-strain curve. The so-obtained $\Delta f'_{cs}$ values of all the 48 FCRC specimens are shown in Figure 9 against the curve depicted by Eq. (14). It is evident that Eq. (14) generally provides reasonably close predictions of the test results for a wide range of effective steel confinement ratios. A relatively large scatter exists for FSCC with a low effective steel confinement ratio, which is believed to be at least partially due to the use of f'_{co} as the intercept stress of FCC.

Stress-Strain Curves

The predictions of the proposed model are compared with typical test results from Eid *et al.* (2009) and Wang *et al.* (2012) in Figure 10. The predictions of existing design-oriented models proposed by Harajli (2006), Eid and Paultre (2008), Pellegrino and Modena (2010), and Wang *et al.* (2012) are also shown in Figure 10 for comparison. As mentioned earlier, the first two of these existing models are typical single-segment stress-strain models while the last two are typical two-segment stress-strain models. Among these models, the ones proposed by Harajli (2006), Pellegrino and Modena (2010) and Wang *et al.* (2012) are for the average axial stress-strain behavior of the concrete in the entire section. These models ignore the clear difference between the core concrete (i.e., FSCC) and the cover concrete which is subjected to FRP confinement only (i.e., FCC), which is a significant disadvantage as in column analysis the cover and the core parts of the section are typically separately treated. To make the comparison with these models possible, the average stress of concrete in an FCRC column instead of the stress of the core concrete (i.e., FSCC) is used in Figures 10 and 11. The experimental average axial stress of concrete in an FCRC column was calculated using the following equation:

$$\sigma_{c,avg} = \frac{P_c - P_s}{A_g - A_s} \quad (25)$$

where P_c is the total axial load carried by the column; P_s is the axial load carried by the longitudinal steel bars; A_g is the gross area of the column section; and A_s is the total area of the longitudinal steel bars. For models which predict different axial stresses for the core concrete and the cover concrete (e.g., the models proposed in the present study), the average axial stress of the entire section was calculated as follows:

$$\sigma_{c,avg} = \frac{\sigma_{core} A_{core} + \sigma_{cover} A_{cover}}{A_{core} + A_{cover}} \quad (26)$$

where σ_{core} and A_{core} are the axial stress and area of the core concrete (excluding the area of longitudinal steel bars) respectively; and σ_{cover} and A_{cover} are the axial stress and area of the cover concrete respectively. The experimental hoop rupture strain of FRP ($\varepsilon_{h,rupt}$) was used to find the ultimate axial strain for all the models.

It is obvious from Figure 10 that the model proposed by Pellegrino and Modena (2010) fails to provide accurate predictions of the test results. Harajli's (2006) model provides reasonable but not accurate predictions of the results presented by Eid *et al.* (2009), and significantly underestimates the ultimate strain of the specimens tested by Wang *et al.* (2012). Wang *et al.*'s (2012) model performs well for their own specimens, but fails to predict the test results presented by Eid *et al.* (2009) especially in terms of the ultimate strain. Eid and Paultre's (2008) model appears to be the most accurate among the existing models, but this model becomes inaccurate for specimens with a relatively high effective steel confinement ratio [Figure 10 (e)-(g)]. It is evident from Figure 10 that the proposed model provides accurate predictions of all the test results, and performs significantly better than all the existing models.

Figure 11 shows a comparison for FSCC in four FCRC specimens tested by Lee *et al.* (2010) which were reinforced with steel spirals of very high yield strength (i.e., 1200 MPa). Lee *et al.*'s (2010) specimens were not used in the development of the model of Teng *et al.* (2014) as the hoop strain data from this study were questionable (Teng *et al.* 2014). As a result, the predictions are terminated at the experimental ultimate axial strain for all the models in Figure 11. It can be seen again that the proposed model performs much better than all the existing models. The proposed model however slightly overestimates the axial stress over the transition portion as the confining pressure from the steel spirals after yielding is directly used in calculating the transition strain defined by Eq. (16), but in reality this confining pressure had to increase gradually from zero to the value at yielding. This issue is not so significant for TSR with a much lower yield stress.

Ultimate State

Figure 12 shows the comparison for ultimate axial strains for all the 48 FCRC specimens, while the comparison for ultimate axial stresses is shown in Figure 13. It is evident that the proposed model provides accurate predictions of the ultimate state of FSCC.

CONCLUSIONS

This paper has presented a three-segment design-oriented stress-strain model for FRP-steel-confined concrete (FSCC) in FRP-confined circular RC columns. The proposed model has been formulated on the basis of extensive numerical results

generated using an accurate analysis-oriented stress-strain model recently proposed by the authors as well as the key characteristics of FSCC as revealed by test results. It consists of a linear initial segment, a curved transition segment, and a linear final segment; the transition segment is smoothly connected to both the initial segment and the final segment. The proposed model reduces to Lam and Teng's well-known stress-strain model for FRP-confined concrete (Lam and Teng 2003; Teng *et al.* 2009) when no confinement from transverse steel exists. The proposed model has been shown to provide accurate predictions of test results and perform significantly better than existing stress-strain models of the same type. The proposed model strikes a good balance between accuracy of prediction and simplicity in form, and its algebraic expressions allow much simpler mathematical manipulations (e.g., differentiations and integrations) than those of the existing models.

It is worth noting that the present paper has been focused on the development of a stress-strain model for FSCC in columns under monotonic concentric axial compression. The extension of the model for use in columns subjected to combined axial compression and bending or cyclic loading is an important subject for future research.

ACKNOWLEDGMENTS

The authors are grateful for the financial support received from the Research Grants Council of the Hong Kong Special Administrative Region (Project No: PolyU 152153/14E), the National Basic Research Program (i.e., 973 Program) (Project Number: 2012CB026200) as well as the Australian Research Council through a *Discovery Early Career Researcher Award* (Project ID: DE140101349) for the second author.

REFERENCES

- ACI 318-08 (2008). *Building Code Requirements for Structural Concrete and Commentary*, American Concrete Institute, Farmington Hills, Michigan, USA.
- ACI 440-08 (2008). *Guide for the Design and Construction of Externally Bonded FRP Systems for Strengthening Concrete Structures*, American Concrete Institute, Farmington Hills, Michigan, USA.
- Braga, F., Gigliotti, R. and Laterza, M. (2006). "Analytical stress-strain relationship for concrete confined by steel stirrups and/or FRP jackets", *Journal of Structural Engineering*, ASCE, Vol. 132, No. 9, pp. 1402-1416.
- Carey, S.A. and Harries, K.A. (2005). "Axial behavior and modeling of confined small-, medium-, and large-scale circular sections with carbon fiber-reinforced polymer jackets", *ACI Structural Journal*, Vol. 102, No. 4, pp. 596-604.
- Chastre, C. and Silva, M.A. (2010). "Monotonic axial behavior and modelling of RC circular columns confined with CFRP", *Engineering Structures*, Vol. 32, No. 8, pp. 2268-2277.
- Concrete Society (2012). *Design Guidance for Strengthening Concrete Structures*

539 *Using Fibre Composite Materials, 3rd Edition*, Technical Rep. No. 55,
540 Crowthorne, Berkshire, U.K.

541 De Luca, A., Nardone, F., Matta, F., Nanni, A., Lignola, G.P. and Prota, A. (2010).
542 “Structural evaluation of full-scale FRP-confined reinforced concrete columns”,
543 *Journal of Composites for Construction*, ASCE, Vol. 15, No. 1, pp. 112-123.

544 Demers, M. and Neale, K.W. (1999). “Confinement of reinforced concrete columns
545 with fibre-reinforced composite sheets-an experimental study”, *Canadian Journal*
546 *of Civil Engineering*, Vol. 26, No. 2, pp. 226-241.

547 Eid, R. and Paultre, P. (2008). “Analytical model for FRP-confined circular reinforced
548 concrete columns”, *Journal of Composites for Construction*, ASCE, Vol. 12, No.
549 5, pp. 541-552.

550 Eid, R., Roy, N. and Paultre, P. (2009). “Normal- and high-strength concrete circular
551 elements wrapped with FRP composites”, *Journal of Composites for*
552 *Construction*, ASCE, Vol. 13, No. 2, pp. 113-124.

553 Esfahani, M. and Kianoush, M. (2005). “Axial compressive strength of reinforced
554 concrete columns wrapped with FRP”, *International Journal of Engineering*
555 *Transactions B: Applications*, Vol. 18, No. 1, pp. 9-19.

556 Fahmy, M.F.M. and Wu, Z. (2010). “Evaluating and proposing models of circular
557 concrete columns confined with different FRP composites”, *Composites Part B:*
558 *Engineering*, Vol. 41, No. 3, pp. 199-213.

559 GB-50608 (2010). *Technical Code for Infrastructure Application of FRP Composites*,
560 Code of China, China Planning Press, Beijing, China.

561 Harajli, M.H. (2006). “Axial stress-strain relationship for FRP confined circular and
562 rectangular concrete columns”, *Cement and Concrete Composites*, Vol. 28, No.
563 10, pp. 938-948.

564 Hollaway, L.C. and Teng, J.G. (2008). *Strengthening and Rehabilitation of Civil*
565 *Infrastructures Using Fibre-Reinforced Polymer (FRP) Composites*, Woodhead
566 Publishing, Cambridge, UK.

567 Hu, H. and Seracino, R. (2013). “Analytical model for FRP-and-steel-confined circular
568 concrete columns in compression”, *Journal of Composites for Construction*,
569 ASCE, Vol. 18, No. 3, pp. A4013012.

570 Ilki, A., Peker, O., Karamuk, E., Demir, C. and Kumbasar, N. (2008). “FRP retrofit of
571 low and medium strength circular and rectangular reinforced concrete columns”,
572 *Journal of Materials in Civil Engineering*, ASCE, Vol. 20, No. 2, pp. 169-188.

573 Jiang, T. and Teng, J.G. (2007). “Analysis-oriented stress-strain models for

FRP-confined concrete”, *Engineering Structures*, Vol. 29, No. 11, pp. 2968-2986.

Lam, L. and Teng, J.G. (2003). “Design-oriented stress-strain model for FRP-confined concrete”, *Construction and Building Materials*, Vol. 17, No. 6, pp. 471-489.

Lee, J.Y., Yi, C.K., Jeong, H.S., Kim, S.W. and Kim, J.K. (2010). “Compressive response of Concrete confined with Steel Spirals and FRP Composites”, *Journal of Composite Materials*, Vol. 44, No. 4, pp. 481-504.

Li, Y.F., Lin, C.T. and Sung, Y.Y. (2003). “A constitutive model for concrete confined with carbon fiber reinforced plastics”, *Mechanics of Materials*, Vol. 35, No. 3, pp. 603-619.

Lin, G., Yu, T. and Teng, J.G. (2015). “On the representation of stress-strain behaviour of concrete under combined FRP and steel confinement”, *12th International Symposium on Fiber Reinforced Polymers for Reinforced Concrete Structures (FRPRCS-12) & 5th Asia-Pacific Conference on Fiber Reinforced Polymers in Structures (APFIS-2015)*, 14-16 December, Nanjing, China.

Lin, H.J. and Liao, C.I. (2004). “Compressive strength of reinforced concrete column confined by composite material”, *Composite Structures*, Vol. 65, No. 2, pp. 239-250.

Mander, J.B., Priestley, M.J. and Park, R. (1988). “Theoretical stress-strain model for confined concrete”, *Journal of Structural Engineering*, ASCE, Vol. 114, No. 8, pp. 1804-1826.

Matthys, S., Toutanji, H., Audenaert, K. and Taerwe, L. (2005). “Axial load behavior of large-scale columns confined with fiber-reinforced polymer composites”, *ACI Structural Journal*, Vol. 102, No. 2, pp. 258-267.

Megalooikonomou, K.G., Monti, G. and Santini, S. (2012). “Constitutive Model for Fiber-Reinforced Polymer-and Tie-Confined Concrete”, *ACI Structural Journal*, Vol. 109, No. 4, pp. 569.

Park, R. and Paulay, T. (1975). *Reinforced Concrete Structures*, Wiley, New York, USA.

Pellegrino, C. and Modena, C. (2010). “Analytical model for FRP confinement of concrete columns with and without internal steel reinforcement”, *Journal of Composites for Construction*, ASCE, Vol. 14, No. 6, pp. 693-705.

Pessiki, S., Harries, K.A., Kestner, J.T., Sause, R. and Ricles, J.M. (2001). “Axial behavior of reinforced concrete columns confined with FRP jackets”, *Journal of Composites for Construction*, ASCE, Vol. 5, No. 4, pp. 237-245.

Popovics, S. (1973). “A numerical approach to the complete stress-strain curve of

concrete”, *Cement and Concrete Research*, Vol. 3, No. 5, pp. 583-599.

Rocca, S. (2007). *Experimental and Analytical Evaluation of FRP-Confined Large Size Reinforced Concrete Columns*, Ph.D. thesis, Civil Engineering, University of Missouri, Rolla, Missouri, USA.

Saatcioglu, M. and Razvi, S.R. (1992). “Strength and ductility of confined concrete”, *Journal of Structural Engineering*, ASCE, Vol. 118, No. 6, pp. 1590-1607.

Samaan, M., Mirmiran, A. and Shahawy, M. (1998). “Model of concrete confined by fiber composites”, *Journal of Structural Engineering*, ASCE, Vol. 124, No. 9, pp. 1025-1031.

Teng, J.G., Chen, J.F., Smith, S.T. and Lam, L. (2002). *FRP Strengthened RC Structures*, John Wiley & Sons, West Sussex, UK.

Teng, J.G., Jiang, T., Lam, L. and Luo, Y.Z. (2009). “Refinement of a design-oriented stress-strain model for FRP-confined concrete”, *Journal of Composites for Construction*, ASCE, Vol. 13, No. 4, pp. 269-278.

Teng, J.G. and Lam, L. (2004). “Behavior and modeling of fiber reinforced polymer-confined concrete”, *Journal of Structural Engineering*, ASCE, Vol. 130, No. 11, pp. 1713-1723.

Teng, J.G., Lin, G. and Yu, T. (2014). “Analysis-oriented stress-strain model for concrete under combined FRP-steel confinement”, *Journal of Composites for Construction*, ASCE, 10.1061/(ASCE)CC.1943-5614.0000549, pp. 04014084.

Wang, Z., Wang, D., Smith, S.T. and Lu, D. (2012). “Experimental testing and analytical modeling of CFRP-confined large circular RC columns subjected to cyclic axial compression”, *Engineering Structures*, Vol. 40, No., pp. 64-74.

Xiao, Y. and Wu, H. (2000). “Compressive behavior of concrete confined by carbon fiber composite jackets”, *Journal of Materials in Civil Engineering*, ASCE, Vol. 12, No. 2, pp. 139-146.

Zhang, Y.X. (2012). *Behavior of Large-Size FRP-Jacketed Circular and Rectangular Reinforced Concrete Columns*, M.Sc. thesis, Department of Civil and Environmental Engineering, The Hong Kong Polytechnic University, Hong Kong, China.

Table 1 Parameters used in the parametric study

Concrete	FRP Jacket		Transverse Steel [*]	
Compressive strength f'_{co} (MPa)	Confinement stiffness ratio ρ_K	Rupture strain $\epsilon_{h, rup}$	Effective confinement stiffness ratio K_{steel} / f'_{co}	Yield stress f_{yh} (MPa)
20-50 at an interval of 10	0.01-0.15 at an interval of 0.005	0.75%, 1.5%, 2.0%	5-125 at an interval of 10	200-800 at an interval of 100

^{*} For Parametric Study 2 only

(a) Type I curve for FSCC

(b) Type II curve for FSCC

Figure 1 Typical stress-strain curves predicted using Teng *et al.*'s (2014) model

Figure 2 Performance of Lam and Teng's model for FSCC

Figure 3 Proposed stress-strain model

Figure 4 Effect of FRP confinement stiffness ratio on E_2

Figure 5 Effect of transverse steel on the transition point of stress-strain curve of FSCC

Figure 6 Increase of intercept stress due to TSR

Figure 7 Simplification of Eq. (20)

Figure 8 Performance of the proposed simplified equation for the ultimate strain

Figure 9 Performance of Eq. (14) for the prediction of the increase of intercept stress due to TSR

(a) Specimen C1H1L2M from Wang *et al.* (2012)

(b) Specimen C1H2L2M from Wang *et al.* (2012)

(c) Specimen C2H1L2M from Wang *et al.* (2012)

(d) Specimen C2H2L2M from Wang *et al.* (2012)

(e) Specimen A3NP2C from Eid *et al.* (2009)

(f) Specimen C2MP4C from Eid *et al.* (2009)

(g) Specimen C2N1P2N from Eid *et al.* (2009)

Figure 10 Performance of models for FSCC in FCRC columns tested by Wang *et al.* (2012) and Eid *et al.* (2009)

(a) Specimen S4F4

(d) Specimen S6F5

Figure 11 Performance of models for FSCC in FCRC columns tested by Lee *et al.* (2010)

Figure 12 Performance of the proposed model in predicting the ultimate axial strain of FSCC

Figure 13 Performance of the proposed model in predicting the ultimate axial stress of FSCC